

Grupo Repol Dinalon® B1S25 MI PA6 Medium Impact

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Impact Grade

Material Notes:

Mechanical properties for Dry As Molded samples Information provided by Grupo Repol

Order this product through the following link:

http://www.lookpolymers.com/polymer_Grupo-Repol-Dinalon-B1S25-MI-PA6-Medium-Impact.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	ISO 1183/A
Moisture Absorption at Equilibrium	<= 0.25 %	<= 0.25 %	Karl-Fischer; ISO 15512/A

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	65.0 MPa	9430 psi	ISO 527
Elongation at Yield	4.0 %	4.0 %	ISO 527
Tensile Modulus	2.40 GPa	348 ksi	ISO 527
Flexural Strength	75.0 MPa	10900 psi	ISO 178
Flexural Modulus	1.60 GPa	232 ksi	ISO 178
Charpy Impact Unnotched	NB @Temperature 23.0 Â°C	NB @Temperature 73.4 Â°F	ISO 179/1eU
Charpy Impact, Notched	1.40 J/cm ² @Temperature 23.0 Â°C	6.66 ft-lb/in ² @Temperature 73.4 Â°F	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	55.0 Â°C	131 Â°F	ISO 75/A
Vicat Softening Point	>= 200 Â°C	>= 392 Â°F	50N; ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China