

Grupo Repol Dinalon® C1S25 PA6/PA66 Blend, Unreinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6/66 , Nylon 66/6, Unreinforced

Material Notes:

Mechanical properties for Dry As Molded samples Information provided by Grupo Repol

Order this product through the following link:

http://www.lookpolymers.com/polymer_Grupo-Repol-Dinalon-C1S25-PA6PA66-Blend-Unreinforced.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ISO 1183/A
Moisture Absorption at Equilibrium	<= 0.25 %	<= 0.25 %	Karl-Fischer; ISO 15512/A

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	80.0 MPa	11600 psi	ISO 527
Elongation at Yield	4.5 %	4.5 %	ISO 527
Tensile Modulus	3.20 GPa	464 ksi	ISO 527
Flexural Strength	90.0 MPa	13100 psi	ISO 178
Flexural Modulus	2.10 GPa	305 ksi	ISO 178
Charpy Impact Unnotched	NB @Temperature 23.0 Â°C	NB @Temperature 73.4 Â°F	ISO 179/1eU
Charpy Impact, Notched	0.450 J/cmÂ² @Temperature 23.0 Â°C	2.14 ft-lb/inÂ² @Temperature 73.4 Â°F	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	60.0 Â°C	140 Â°F	ISO 75/A
Vicat Softening Point	>= 200 Â°C	>= 392 Â°F	50N; ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China