

Gwent Electronic Materials D2070423D5 Polymer Dielectric

Category : Fluid , Polymer

Material Notes:

Grey colored screen printable polymer dielectric, suitable for defining electrode areas and forms a protective layer over the electrode tracking during immersion of the electrode. The formulation is designed for maximum flexibility. Screen Printing Equipment: semi-automatic, automaticScreen Types: stainless steel, polyester, mesh 156-325tpiSubstrate: Polyester, PVC, Polycarbonate, Ceramic or Alumina.Information provided by Gwent Electronic Materials Ltd.

Order this product through the following link:
http://www.lookpolymers.com/polymer_Gwent-Electronic-Materials-D2070423D5-Polymer-Dielectric.php

Physical Properties	Metric	English	Comments
Solids Content	43 - 45 %	43 - 45 %	
	@Temperature 150 Â°C	@Temperature 302 Â°F	
Viscosity	14000 - 16000 cP	14000 - 16000 cP	Haake VT 550 PK1.1Â°
	@Shear Rate 230 1/s, Temperature 25.0 Â°C	@Shear Rate 230 1/s, Temperature 77.0 Â°F	
Storage Temperature	20.0 Â°C	68.0 Â°F	sealed container

Processing Properties	Metric	English	Comments
Cure Time	15.0 min	0.250 hour	
	@Temperature 130 Â°C	@Temperature 266 Â°F	
	30.0 min	0.500 hour	
	@Temperature 80.0 Â°C	@Temperature 176 Â°F	
Shelf Life	6.00 Month	6.00 Month	

Descriptive Properties	Value	Comments
Coverage cm2/g	305	Using a 230 mesh stainless steel screen with 13 micron emulsion
Solvent Resistance	Acetone	Attack
	Acetone	Attack
	DMAC	Attack
	DMAC	Attack
	DMF	Attack
	DMF	Attack

Descriptive Properties	Value	Comments
	MEK	Full Attack
	THF	Attack
	THF	Attack

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China