

## H.C. Starck Baymetec® Niobium Ethoxide

Category : Ceramic , Oxide

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_HC-Starck-Baymetec-Niobium-Ethoxide.php](http://www.lookpolymers.com/polymer_HC-Starck-Baymetec-Niobium-Ethoxide.php)

| Physical Properties | Metric    | English                   | Comments |
|---------------------|-----------|---------------------------|----------|
| Density             | 1.32 g/cc | 0.0477 lb/in <sup>3</sup> |          |

| Thermal Properties        | Metric  | English | Comments |
|---------------------------|---------|---------|----------|
| Melting Point             | 6.00 °C | 42.8 °F |          |
| Boiling Point             | 133 °C  | 271 °F  | .13 hPa  |
| Decomposition Temperature | 200 °C  | 392 °F  |          |

| Descriptive Properties | Value           | Comments |
|------------------------|-----------------|----------|
| Color                  | slightly yellow |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China