

Hannam Chemical Hanalac H-2938 ABS

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hannam-Chemical-Hanalac-H-2938-ABS.php

Physical Properties	Metric	English	Comments
Melt Flow	2.3 g/10 min	2.3 g/10 min	ASTM D1238G

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	106	106	ASTM D785
Tensile Strength, Ultimate	48.0 MPa	6960 psi	ASTM D638
Elongation at Break	25 %	25 %	ASTM D638
Flexural Yield Strength	68.6 MPa	9950 psi	ASTM D790
Flexural Modulus	2.26 GPa	328 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	97.0 Â°C	207 Â°F	Heat Distortion Temp
Deflection Temperature at 1.8 MPa (264 psi)	97.0 Â°C	207 Â°F	ASTM D648
Vicat Softening Point	115 Â°C	239 Â°F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China