

## Haynes 230® alloy plate

Category : Metal , Nonferrous Metal , Nickel Alloy , Superalloy

### Material Notes:

Excellent high-temperature strength, outstanding resistance to oxidizing environments up to 1149°C, premier resistance to nitriding environments, and excellent long-term thermal stability. Applications include combustion cans, transition ducts, flameholders, thermocouple sheaths and other gas turbine components; used for catalyst grid supports in ammonia burners, high-strength thermocouple protection tubes, high-temperature heat exchangers, ducts, high-temperature bellows; furnace retorts, chains and fixtures, burner flame shrouds, recuperator internals, dampers, nitriding furnace internals, heat-treating baskets, grates, trays, sparger tubes, and cyclone internals. Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Haynes-230-alloy-plate.php](http://www.lookpolymers.com/polymer_Haynes-230-alloy-plate.php)

| Physical Properties | Metric    | English                  | Comments |
|---------------------|-----------|--------------------------|----------|
| Density             | 8.97 g/cc | 0.324 lb/in <sup>3</sup> | at RT    |

| Mechanical Properties      | Metric                          | English                           | Comments   |
|----------------------------|---------------------------------|-----------------------------------|------------|
| Tensile Strength, Ultimate | 850 MPa                         | 123000 psi                        |            |
| Tensile Strength, Yield    | 405 MPa<br>@Strain 0.200 %      | 58700 psi<br>@Strain 0.200 %      |            |
| Elongation at Break        | 51 %                            | 51 %                              | in 50.8 mm |
| Modulus of Elasticity      | 211 GPa                         | 30600 ksi                         | RT         |
|                            | 150 GPa<br>@Temperature 1000 °C | 21800 ksi<br>@Temperature 1830 °F |            |
|                            | 157 GPa<br>@Temperature 900 °C  | 22800 ksi<br>@Temperature 1650 °F |            |
|                            | 164 GPa<br>@Temperature 800 °C  | 23800 ksi<br>@Temperature 1470 °F |            |
|                            | 171 GPa<br>@Temperature 700 °C  | 24800 ksi<br>@Temperature 1290 °F |            |
|                            | 177 GPa<br>@Temperature 600 °C  | 25700 ksi<br>@Temperature 1110 °F |            |

| Mechanical Properties | Metric               | English              | Comments |
|-----------------------|----------------------|----------------------|----------|
|                       | @Temperature 500 Â°C | @Temperature 932 Â°F |          |
|                       | 190 GPa              | 27600 ksi            |          |
|                       | @Temperature 400 Â°C | @Temperature 752 Â°F |          |
|                       | 196 GPa              | 28400 ksi            |          |
|                       | @Temperature 300 Â°C | @Temperature 572 Â°F |          |
|                       | 202 GPa              | 29300 ksi            |          |
|                       | @Temperature 200 Â°C | @Temperature 392 Â°F |          |
|                       | 207 GPa              | 30000 ksi            |          |
|                       | @Temperature 100 Â°C | @Temperature 212 Â°F |          |
| Charpy Impact         | 73.0 J               | 53.8 ft-lb           |          |

| Thermal Properties | Metric                      | English                      | Comments |
|--------------------|-----------------------------|------------------------------|----------|
| CTE, linear        | 12.7 Âµm/m-Â°C              | 7.06 Âµin/in-Â°F             |          |
|                    | @Temperature 25.0 - 100 Â°C | @Temperature 77.0 - 212 Â°F  |          |
|                    | 13.0 Âµm/m-Â°C              | 7.22 Âµin/in-Â°F             |          |
|                    | @Temperature 25.0 - 200 Â°C | @Temperature 77.0 - 392 Â°F  |          |
|                    | 13.3 Âµm/m-Â°C              | 7.39 Âµin/in-Â°F             |          |
|                    | @Temperature 25.0 - 300 Â°C | @Temperature 77.0 - 572 Â°F  |          |
|                    | 13.7 Âµm/m-Â°C              | 7.61 Âµin/in-Â°F             |          |
|                    | @Temperature 25.0 - 400 Â°C | @Temperature 77.0 - 752 Â°F  |          |
|                    | 14.0 Âµm/m-Â°C              | 7.78 Âµin/in-Â°F             |          |
|                    | @Temperature 25.0 - 500 Â°C | @Temperature 77.0 - 932 Â°F  |          |
|                    | 14.4 Âµm/m-Â°C              | 8.00 Âµin/in-Â°F             |          |
|                    | @Temperature 25.0 - 600 Â°C | @Temperature 77.0 - 1110 Â°F |          |
|                    | 14.8 Âµm/m-Â°C              | 8.22 Âµin/in-Â°F             |          |
|                    | @Temperature 25.0 - 700 Â°C | @Temperature 77.0 - 1290 Â°F |          |
|                    | 15.2 Âµm/m-Â°C              | 8.44 Âµin/in-Â°F             |          |

| Thermal Properties     | Metric<br>@Temperature 25.0 -<br>900 Â°C          | English<br>@Temperature 77.0 -<br>1650 Â°F          | Comments |
|------------------------|---------------------------------------------------|-----------------------------------------------------|----------|
|                        | 15.7 Âµm/m-Â°C<br>@Temperature 25.0 -<br>900 Â°C  | 8.72 Âµin/in-Â°F<br>@Temperature 77.0 -<br>1650 Â°F |          |
|                        | 16.1 Âµm/m-Â°C<br>@Temperature 25.0 -<br>1000 Â°C | 8.94 Âµin/in-Â°F<br>@Temperature 77.0 -<br>1830 Â°F |          |
| Specific Heat Capacity | 0.397 J/g-Â°C                                     | 0.0949 BTU/lb-Â°F                                   | RT       |
|                        | 0.419 J/g-Â°C<br>@Temperature 100 Â°C             | 0.100 BTU/lb-Â°F<br>@Temperature 212 Â°F            |          |
|                        | 0.435 J/g-Â°C<br>@Temperature 200 Â°C             | 0.104 BTU/lb-Â°F<br>@Temperature 392 Â°F            |          |
|                        | 0.448 J/g-Â°C<br>@Temperature 300 Â°C             | 0.107 BTU/lb-Â°F<br>@Temperature 572 Â°F            |          |
|                        | 0.465 J/g-Â°C<br>@Temperature 400 Â°C             | 0.111 BTU/lb-Â°F<br>@Temperature 752 Â°F            |          |
|                        | 0.473 J/g-Â°C<br>@Temperature 500 Â°C             | 0.113 BTU/lb-Â°F<br>@Temperature 932 Â°F            |          |
|                        | 0.486 J/g-Â°C<br>@Temperature 600 Â°C             | 0.116 BTU/lb-Â°F<br>@Temperature 1110<br>Â°F        |          |
|                        | 0.574 J/g-Â°C<br>@Temperature 700 Â°C             | 0.137 BTU/lb-Â°F<br>@Temperature 1290<br>Â°F        |          |
|                        | 0.595 J/g-Â°C<br>@Temperature 800 Â°C             | 0.142 BTU/lb-Â°F<br>@Temperature 1470<br>Â°F        |          |
|                        | 0.609 J/g-Â°C<br>@Temperature 900 Â°C             | 0.146 BTU/lb-Â°F<br>@Temperature 1650<br>Â°F        |          |
|                        | 0.617 J/g-Â°C<br>@Temperature 1000<br>Â°C         | 0.147 BTU/lb-Â°F<br>@Temperature 1830<br>Â°F        |          |
| Thermal Conductivity   | 8.90 W/m-K                                        | 61.8 BTU-in/hr-ftÂ²-<br>Â°F                         | RT       |

| Thermal Properties | Metric                | English                 | Comments |
|--------------------|-----------------------|-------------------------|----------|
|                    | 10.4 W/m-K            | 86.1 BTU-in/hr-ftÂ²-Â°F |          |
|                    | @Temperature 100 Â°C  | @Temperature 212 Â°F    |          |
|                    | 12.4 W/m-K            | 86.1 BTU-in/hr-ftÂ²-Â°F |          |
|                    | @Temperature 200 Â°C  | @Temperature 392 Â°F    |          |
|                    | 14.4 W/m-K            | 99.9 BTU-in/hr-ftÂ²-Â°F |          |
|                    | @Temperature 300 Â°C  | @Temperature 572 Â°F    |          |
|                    | 16.4 W/m-K            | 114 BTU-in/hr-ftÂ²-Â°F  |          |
|                    | @Temperature 400 Â°C  | @Temperature 752 Â°F    |          |
|                    | 18.4 W/m-K            | 128 BTU-in/hr-ftÂ²-Â°F  |          |
|                    | @Temperature 500 Â°C  | @Temperature 932 Â°F    |          |
|                    | 20.4 W/m-K            | 142 BTU-in/hr-ftÂ²-Â°F  |          |
|                    | @Temperature 600 Â°C  | @Temperature 1110 Â°F   |          |
|                    | 22.4 W/m-K            | 155 BTU-in/hr-ftÂ²-Â°F  |          |
|                    | @Temperature 700 Â°C  | @Temperature 1290 Â°F   |          |
|                    | 24.4 W/m-K            | 169 BTU-in/hr-ftÂ²-Â°F  |          |
|                    | @Temperature 800 Â°C  | @Temperature 1470 Â°F   |          |
|                    | 26.4 W/m-K            | 183 BTU-in/hr-ftÂ²-Â°F  |          |
|                    | @Temperature 900 Â°C  | @Temperature 1650 Â°F   |          |
|                    | 28.4 W/m-K            | 197 BTU-in/hr-ftÂ²-Â°F  |          |
|                    | @Temperature 1000 Â°C | @Temperature 1830 Â°F   |          |
| Melting Point      | 1301 - 1371 Â°C       | 2374 - 2500 Â°F         |          |
| Solidus            | 1301 Â°C              | 2374 Â°F                |          |
| Liquidus           | 1371 Â°C              | 2500 Â°F                |          |

| Component Elements Properties | Metric     | English    | Comments |
|-------------------------------|------------|------------|----------|
| Aluminum, Al                  | 0.30 %     | 0.30 %     |          |
| Boron, B                      | <= 0.015 % | <= 0.015 % |          |

| Carbon C<br>Component Elements Properties | 0.10 %<br>Metric | 0.10 %<br>English | Comments |
|-------------------------------------------|------------------|-------------------|----------|
| Chromium, Cr                              | 22 %             | 22 %              |          |
| Cobalt, Co                                | <= 5.0 %         | <= 5.0 %          |          |
| Iron, Fe                                  | <= 3.0 %         | <= 3.0 %          |          |
| Lanthanum, La                             | 0.020 %          | 0.020 %           |          |

| Electrical Properties  | Metric                   | English                  | Comments |
|------------------------|--------------------------|--------------------------|----------|
| Electrical Resistivity | 0.000125 ohm-cm          | 0.000125 ohm-cm          | RT       |
|                        | 0.000125 ohm-cm          | 0.000125 ohm-cm          |          |
|                        | @Temperature 1000<br>Â°C | @Temperature 1830<br>Â°F |          |
|                        | 0.0001258 ohm-cm         | 0.0001258 ohm-cm         |          |
|                        | @Temperature 100 Â°C     | @Temperature 212 Â°F     |          |
|                        | 0.0001265 ohm-cm         | 0.0001265 ohm-cm         |          |
|                        | @Temperature 200 Â°C     | @Temperature 392 Â°F     |          |
|                        | 0.0001271 ohm-cm         | 0.0001271 ohm-cm         |          |
|                        | @Temperature 900 Â°C     | @Temperature 1650<br>Â°F |          |
|                        | 0.0001273 ohm-cm         | 0.0001273 ohm-cm         |          |
|                        | @Temperature 300 Â°C     | @Temperature 572 Â°F     |          |
|                        | 0.0001284 ohm-cm         | 0.0001284 ohm-cm         |          |
|                        | @Temperature 400 Â°C     | @Temperature 752 Â°F     |          |
|                        | 0.0001291 ohm-cm         | 0.0001291 ohm-cm         |          |
|                        | @Temperature 800 Â°C     | @Temperature 1470<br>Â°F |          |
|                        | 0.0001302 ohm-cm         | 0.0001302 ohm-cm         |          |
|                        | @Temperature 500 Â°C     | @Temperature 932 Â°F     |          |
|                        | 0.0001307 ohm-cm         | 0.0001307 ohm-cm         |          |
|                        | @Temperature 700 Â°C     | @Temperature 1290<br>Â°F |          |
|                        | 0.0001312 ohm-cm         | 0.0001312 ohm-cm         |          |
|                        | @Temperature 600 Â°C     | @Temperature 1110<br>Â°F |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China