

Haynes 25 alloy, cold rolled and 1205Â°C (2200Â°F) solution annealed sheet

Category : Metal , Nonferrous Metal , Cobalt Alloy , Superalloy

Material Notes:

Excellent high-temperature strength with good resistance to oxidizing environments up to 980Â°C for prolonged exposures and excellent resistance to sulfidation and excellent resistance to metal galling. Applications in the aerospace industry, including parts in military and commercial gas turbine engines. Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Haynes-25-alloy-cold-rolled-and-1205C-2200F-solution-annealed-sheet.php

Physical Properties	Metric	English	Comments
Density	9.13 g/cc	0.330 lb/inÂ³	at RT

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	1005 MPa	145800 psi	
	160 MPa	23200 psi	
	@Temperature 1095 Â°C	@Temperature 2003 Â°F	
	235 MPa	34100 psi	
	@Temperature 980 Â°C	@Temperature 1800 Â°F	
	415 MPa	60200 psi	
	@Temperature 870 Â°C	@Temperature 1600 Â°F	
	640 MPa	92800 psi	
	@Temperature 760 Â°C	@Temperature 1400 Â°F	
	745 MPa	108000 psi	
	@Temperature 650 Â°C	@Temperature 1200 Â°F	
Tensile Strength, Yield	770 MPa	112000 psi	
	@Temperature 540 Â°C	@Temperature 1000 Â°F	
	475 MPa	68900 psi	
	@Strain 0.200 %	@Strain 0.200 %	
	76.0 MPa	11000 psi	
	@Strain 0.200 %, Temperature 1095 Â°C	@Strain 0.200 %, Temperature 2003 Â°F	

Mechanical Properties	Metric	English	Comments
	123 MPa @Strain 0.200 %, Temperature 980 Â°C	18000 psi @Strain 0.200 %, Temperature 1800 Â°F	
	250 MPa @Strain 0.200 %, Temperature 870 Â°C	36300 psi @Strain 0.200 %, Temperature 1600 Â°F	
	285 MPa @Strain 0.200 %, Temperature 760 Â°C	41300 psi @Strain 0.200 %, Temperature 1400 Â°F	
	330 MPa @Strain 0.200 %, Temperature 540 Â°C	47900 psi @Strain 0.200 %, Temperature 1000 Â°F	
	330 MPa @Strain 0.200 %, Temperature 650 Â°C	47900 psi @Strain 0.200 %, Temperature 1200 Â°F	
Elongation at Break	51 %	51 %	in 51 mm
	36 % @Temperature 980 Â°C	36 % @Temperature 1800 Â°F	in 51 mm
	42 % @Temperature 760 Â°C	42 % @Temperature 1400 Â°F	in 51 mm
	45 % @Temperature 870 Â°C	45 % @Temperature 1600 Â°F	in 51 mm
	48 % @Temperature 1095 Â°C	48 % @Temperature 2003 Â°F	in 51 mm
	60 % @Temperature 540 Â°C	60 % @Temperature 1000 Â°F	in 51 mm
	60 % @Temperature 650 Â°C	60 % @Temperature 1200 Â°F	in 51 mm
Modulus of Elasticity	225 GPa	32600 ksi	RT
	146 GPa	21200 ksi	

Mechanical Properties	@Temperature 1000 Metric °C	@Temperature 1830 English °F	Comments
	154 GPa	22300 ksi	
	@Temperature 900 °C	@Temperature 1650 °F	
	163 GPa	23600 ksi	
	@Temperature 800 °C	@Temperature 1470 °F	
	174 GPa	25200 ksi	
	@Temperature 700 °C	@Temperature 1290 °F	
	181 GPa	26300 ksi	
	@Temperature 600 °C	@Temperature 1110 °F	
	188 GPa	27300 ksi	
	@Temperature 500 °C	@Temperature 932 °F	
	197 GPa	28600 ksi	
	@Temperature 400 °C	@Temperature 752 °F	
	204 GPa	29600 ksi	
	@Temperature 300 °C	@Temperature 572 °F	
	214 GPa	31000 ksi	
	@Temperature 200 °C	@Temperature 392 °F	
	222 GPa	32200 ksi	
	@Temperature 100 °C	@Temperature 212 °F	
Charpy Impact	262 J	193 ft-lb	
	144 J	106 ft-lb	
	@Temperature 980 °C	@Temperature 1800 °F	
	148 J	109 ft-lb	
	@Temperature -196 °C	@Temperature -321 °F	
	163 J	120 ft-lb	
	@Temperature 870 °C	@Temperature 1600 °F	
	182 J	134 ft-lb	

Mechanical Properties	Metric @Temperature -138 Â°C	English @Temperature -216 Â°F	Comments
	194 J	143 ft-lb	
	@Temperature 760 Â°C	@Temperature 1400 Â°F	
	212 J	156 ft-lb	
	@Temperature -78.0 Â°C	@Temperature -108 Â°F	
	230 J	170 ft-lb	
	@Temperature 650 Â°C	@Temperature 1200 Â°F	
	243 J	179 ft-lb	
	@Temperature -29.0 Â°C	@Temperature -20.2 Â°F	
	273 J	201 ft-lb	
	@Temperature 540 Â°C	@Temperature 1000 Â°F	
	297 J	219 ft-lb	
	@Temperature 260 Â°C	@Temperature 500 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear	12.3 Âµm/m-Â°C	6.83 Âµin/in-Â°F	
	@Temperature 25.0 - 100 Â°C	@Temperature 77.0 - 212 Â°F	
	12.9 Âµm/m-Â°C	7.17 Âµin/in-Â°F	
	@Temperature 25.0 - 200 Â°C	@Temperature 77.0 - 392 Â°F	
	13.6 Âµm/m-Â°C	7.56 Âµin/in-Â°F	
	@Temperature 25.0 - 300 Â°C	@Temperature 77.0 - 572 Â°F	
	14.3 Âµm/m-Â°C	7.94 Âµin/in-Â°F	
	@Temperature 25.0 - 500 Â°C	@Temperature 77.0 - 932 Â°F	
	14.3 Âµm/m-Â°C	7.94 Âµin/in-Â°F	
	@Temperature 25.0 - 400 Â°C	@Temperature 77.0 - 752 Â°F	
	14.6 Âµm/m-Â°C	8.11 Âµin/in-Â°F	
	@Temperature 25.0 -	@Temperature 77.0 -	

Thermal Properties	600 Â°C Metric	1110 Â°F English	Comments
	15.1 Âµm/m-Â°C	8.39 Âµin/in-Â°F	
	@Temperature 25.0 - 700 Â°C	@Temperature 77.0 - 1290 Â°F	
	15.8 Âµm/m-Â°C	8.78 Âµin/in-Â°F	
	@Temperature 25.0 - 800 Â°C	@Temperature 77.0 - 1470 Â°F	
	16.5 Âµm/m-Â°C	9.17 Âµin/in-Â°F	
	@Temperature 25.0 - 900 Â°C	@Temperature 77.0 - 1650 Â°F	
	17.0 Âµm/m-Â°C	9.44 Âµin/in-Â°F	
	@Temperature 25.0 - 1000 Â°C	@Temperature 77.0 - 1830 Â°F	
Thermal Conductivity	9.40 W/m-K	65.2 BTU-in/hr-ftÂ²-Â°F	RT
	10.9 W/m-K	75.6 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 100 Â°C	@Temperature 212 Â°F	
	12.9 W/m-K	89.5 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 200 Â°C	@Temperature 392 Â°F	
	14.8 W/m-K	103 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 300 Â°C	@Temperature 572 Â°F	
	16.8 W/m-K	117 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 400 Â°C	@Temperature 752 Â°F	
	18.7 W/m-K	130 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 500 Â°C	@Temperature 932 Â°F	
	20.7 W/m-K	144 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 600 Â°C	@Temperature 1110 Â°F	
	22.6 W/m-K	157 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 700 Â°C	@Temperature 1290 Â°F	
	24.7 W/m-K	171 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 800 Â°C	@Temperature 1470 Â°F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000886 ohm-cm	0.0000886 ohm-cm	RT
	0.0000950 ohm-cm	0.0000950 ohm-cm	
	@Temperature 1000 Â°C	@Temperature 1830 Â°F	
	0.0001011 ohm-cm	0.0001011 ohm-cm	
	@Temperature 900 Â°C	@Temperature 1650 Â°F	
	0.0001066 ohm-cm	0.0001066 ohm-cm	
	@Temperature 700 Â°C	@Temperature 1290 Â°F	
	0.0001078 ohm-cm	0.0001078 ohm-cm	
	@Temperature 800 Â°C	@Temperature 1470 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China