

Haynes 25 alloy, cold worked sheet, 20% cold reduction, aged at 595Â°C (1100Â°F) for 2 hours

Category : Metal , Nonferrous Metal , Cobalt Alloy , Superalloy

Material Notes:

Excellent high-temperature strength with good resistance to oxidizing environments up to 980Â°C for prolonged exposures and excellent resistance to sulfidation and excellent resistance to metal galling. Applications in the aerospace industry, including parts in military and commercial gas turbine engines. Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Haynes-25-alloy-cold-worked-sheet-20-cold-reduction-aged-at-595C-1100F-for-2-hours.php

Physical Properties	Metric	English	Comments
Density	9.13 g/cc	0.330 lb/inÂ³	at RT

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	1315 MPa	190700 psi	
	290 MPa	42100 psi	
	@Temperature 980 Â°C	@Temperature 1800 Â°F	
	490 MPa	71100 psi	
	@Temperature 870 Â°C	@Temperature 1600 Â°F	
	800 MPa	116000 psi	
	@Temperature 760 Â°C	@Temperature 1400 Â°F	
Tensile Strength, Yield	965 MPa	140000 psi	
	@Temperature 650 Â°C	@Temperature 1200 Â°F	
	1025 MPa	148700 psi	
	@Temperature 540 Â°C	@Temperature 1000 Â°F	
	1140 MPa	165000 psi	
	@Temperature 315 Â°C	@Temperature 599 Â°F	
	1115 MPa	161700 psi	
	@Strain 0.200 %	@Strain 0.200 %	
	215 MPa	31200 psi	
	@Strain 0.200 %,	@Strain 0.200 %,	

Mechanical Properties	Temperature 980 Â°C Metric	Temperature 1800 Â°F English	Comments
	345 MPa	50000 psi	
	@Strain 0.200 %, Temperature 870 Â°C	@Strain 0.200 %, Temperature 1600 Â°F	
	635 MPa	92100 psi	
	@Strain 0.200 %, Temperature 760 Â°C	@Strain 0.200 %, Temperature 1400 Â°F	
	820 MPa	119000 psi	
	@Strain 0.200 %, Temperature 650 Â°C	@Strain 0.200 %, Temperature 1200 Â°F	
	855 MPa	124000 psi	
	@Strain 0.200 %, Temperature 540 Â°C	@Strain 0.200 %, Temperature 1000 Â°F	
	910 MPa	132000 psi	
	@Strain 0.200 %, Temperature 315 Â°C	@Strain 0.200 %, Temperature 599 Â°F	
Elongation at Break	16 %	16 %	in 51 mm
	7.0 %	7.0 %	
	@Temperature 760 Â°C	@Temperature 1400 Â°F	in 51 mm
	9.0 %	9.0 %	
	@Temperature 870 Â°C	@Temperature 1600 Â°F	in 51 mm
	12 %	12 %	
	@Temperature 980 Â°C	@Temperature 1800 Â°F	in 51 mm
	13 %	13 %	
	@Temperature 650 Â°C	@Temperature 1200 Â°F	in 51 mm
	23 %	23 %	
	@Temperature 540 Â°C	@Temperature 1000 Â°F	in 51 mm
	28 %	28 %	
	@Temperature 315 Â°C	@Temperature 599 Â°F	in 51 mm
Modulus of Elasticity	225 GPa	32600 ksi	RT
	146 GPa	21200 ksi	

Mechanical Properties	@Temperature 1000 Metric °C	@Temperature 1830 English °F	Comments
	154 GPa	22300 ksi	
	@Temperature 900 °C	@Temperature 1650 °F	
	163 GPa	23600 ksi	
	@Temperature 800 °C	@Temperature 1470 °F	
	174 GPa	25200 ksi	
	@Temperature 700 °C	@Temperature 1290 °F	
	181 GPa	26300 ksi	
	@Temperature 600 °C	@Temperature 1110 °F	
	188 GPa	27300 ksi	
	@Temperature 500 °C	@Temperature 932 °F	
	197 GPa	28600 ksi	
	@Temperature 400 °C	@Temperature 752 °F	
	204 GPa	29600 ksi	
	@Temperature 300 °C	@Temperature 572 °F	
	214 GPa	31000 ksi	
	@Temperature 200 °C	@Temperature 392 °F	
	222 GPa	32200 ksi	
	@Temperature 100 °C	@Temperature 212 °F	
Charpy Impact	262 J	193 ft-lb	
	144 J	106 ft-lb	
	@Temperature 980 °C	@Temperature 1800 °F	
	148 J	109 ft-lb	
	@Temperature -196 °C	@Temperature -321 °F	
	163 J	120 ft-lb	
	@Temperature 870 °C	@Temperature 1600 °F	
	182 J	134 ft-lb	
	@Temperature -138	@Temperature -216	

Mechanical Properties	°C Metric	°F English	Comments
	194 J	143 ft-lb	
	@Temperature 760 °C	@Temperature 1400 °F	
	212 J	156 ft-lb	
	@Temperature -78.0 °C	@Temperature -108 °F	
	230 J	170 ft-lb	
	@Temperature 650 °C	@Temperature 1200 °F	
	243 J	179 ft-lb	
	@Temperature -29.0 °C	@Temperature -20.2 °F	
	273 J	201 ft-lb	
	@Temperature 540 °C	@Temperature 1000 °F	
	297 J	219 ft-lb	
	@Temperature 260 °C	@Temperature 500 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	12.3 µm/m-°C	6.83 µin/in-°F	
	@Temperature 25.0 - 100 °C	@Temperature 77.0 - 212 °F	
	12.9 µm/m-°C	7.17 µin/in-°F	
	@Temperature 25.0 - 200 °C	@Temperature 77.0 - 392 °F	
	13.6 µm/m-°C	7.56 µin/in-°F	
	@Temperature 25.0 - 300 °C	@Temperature 77.0 - 572 °F	
	14.3 µm/m-°C	7.94 µin/in-°F	
	@Temperature 25.0 - 500 °C	@Temperature 77.0 - 932 °F	
	14.3 µm/m-°C	7.94 µin/in-°F	
	@Temperature 25.0 - 400 °C	@Temperature 77.0 - 752 °F	
	14.6 µm/m-°C	8.11 µin/in-°F	
	@Temperature 25.0 -	@Temperature 77.0 -	

Thermal Properties	600 Â°C Metric	1110 Â°F English	Comments
	15.1 Âµm/m-Â°C	8.39 Âµin/in-Â°F	
	@Temperature 25.0 - 700 Â°C	@Temperature 77.0 - 1290 Â°F	
	15.8 Âµm/m-Â°C	8.78 Âµin/in-Â°F	
	@Temperature 25.0 - 800 Â°C	@Temperature 77.0 - 1470 Â°F	
	16.5 Âµm/m-Â°C	9.17 Âµin/in-Â°F	
	@Temperature 25.0 - 900 Â°C	@Temperature 77.0 - 1650 Â°F	
	17.0 Âµm/m-Â°C	9.44 Âµin/in-Â°F	
	@Temperature 25.0 - 1000 Â°C	@Temperature 77.0 - 1830 Â°F	
Thermal Conductivity	9.40 W/m-K	65.2 BTU-in/hr-ftÂ²-Â°F	RT
	10.9 W/m-K	75.6 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 100 Â°C	@Temperature 212 Â°F	
	12.9 W/m-K	89.5 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 200 Â°C	@Temperature 392 Â°F	
	14.8 W/m-K	103 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 300 Â°C	@Temperature 572 Â°F	
	16.8 W/m-K	117 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 400 Â°C	@Temperature 752 Â°F	
	18.7 W/m-K	130 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 500 Â°C	@Temperature 932 Â°F	
	20.7 W/m-K	144 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 600 Â°C	@Temperature 1110 Â°F	
	22.6 W/m-K	157 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 700 Â°C	@Temperature 1290 Â°F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000886 ohm-cm	0.0000886 ohm-cm	RT

Electrical Properties	0.0000950 ohm-cm Metric	0.0000950 ohm-cm English	Comments
	@Temperature 1000 °C	@Temperature 1830 °F	
	0.0001011 ohm-cm	0.0001011 ohm-cm	
	@Temperature 900 °C	@Temperature 1650 °F	
	0.0001066 ohm-cm	0.0001066 ohm-cm	
	@Temperature 700 °C	@Temperature 1290 °F	
	0.0001078 ohm-cm	0.0001078 ohm-cm	
	@Temperature 800 °C	@Temperature 1470 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China