

Haynes Hastelloy® C-2000® Nickel Alloy Shielded Metal Arc Welded (SMAW) All Weld Cruciform

Category : Metal , Nonferrous Metal , Nickel Alloy

Material Notes:

Nickel-chromium-molybdenum (Ni-Cr-Mo) C-type alloys have a long history of use in the Chemical Process Industries and are known for their versatility. Not only do they resist all acids (especially hydrochloric, sulfuric, and hydrofluoric) over large temperature ranges, but they also resist the insidious types of attack induced by chlorides and other halide solutions, specifically pitting, crevice attack, and stress corrosion cracking. HASTELLOY® C-2000® alloy has greater versatility than traditional Ni-Cr-Mo alloys. This was accomplished by use of a high chromium content, a high molybdenum content, and a small but effective addition of copper. The copper provides enhanced temperature capability in sulfuric acid, hydrofluoric acid, and dilute hydrochloric acid. C-2000 alloy is available in plate, sheet, strip, billet, bar, wire, covered electrodes, pipe, and tubing. Applications: Chemical process industry reactors, heat exchangers, columns, and piping. Pharmaceutical industry reactors and dryers. Flue gas desulfurization systems. C-2000 alloy is covered by ASME, ASTM, AWS, DIN, and TÜV specifications. Welding: The weldability of C-2000 alloy is similar to that of C-276 alloy. To weld the C-type alloys, three processes are commonly used. For sheet welds and plate root passes, gas tungsten arc (GTAW) welding is favored. For plate welds, the gas metal arc (GMAW) process is preferred. For field welding, the shielded metal arc process, using coated electrodes, is favored. Submerged arc welding is not recommended as this process is characterized by high heat input to the base metal and slow cooling of the weld. To minimize the precipitation of second phases in regions affected by the heat of welding, a maximum interpass temperature of 93°C (200°F) is recommended for the C-type alloys. Welding of cold-worked materials is strongly discouraged, since they sensitize more quickly and induce residual stresses. A full solution anneal, followed by water quenching, is recommended for cold-worked structures prior to welding. Base Metal Preparation: The joint surface and adjacent area should be thoroughly cleaned before welding. All grease, oil, crayon marks, sulfur compounds, and other foreign matter should be removed. Filler Metal Selections: For gas tungsten arc and gas metal arc welding, C-2000 filler wire (ERNiCrMo-17) is suggested. For shielded metal arc welding, C-2000 covered electrodes (ENiCrMo-17) are suggested. Heat Treatment: The standard solution annealing treatment consists of heating to 1135°C (2075°F) followed by rapid air-cooling or water quenching. Parts which have been hot formed should be solution annealed prior to final fabrication or installation. Forming: C-2000 alloy has excellent forming characteristics, and cold forming is the preferred method of shaping. The alloy can be easily cold worked due to its good ductility. The alloy is generally stiffer than the austenitic stainless steels so more energy is required during cold forming. Tensile and impact properties reported are for welded samples. Other properties are typical of the alloy. Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Haynes-Hastelloy-C-2000-Nickel-Alloy-Shielded-Metal-Arc-Welded-SMAW-All-Weld-Cruciform.php

Physical Properties	Metric	English	Comments
Density	8.50 g/cc	0.307 lb/in³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	565 MPa @Diameter 12.7 mm, Temperature 450 °C	81900 psi @Diameter 0.500 in, Temperature 842 °F	

Mechanical Properties	744 MPa Metric	108000 psi English	Comments
	@Diameter 12.7 mm, Temperature 25.0 °C	@Diameter 0.500 in, Temperature 77.0 °F	
Tensile Strength, Yield	386 MPa	56000 psi	
	@Diameter 12.7 mm, Temperature 450 °C	@Diameter 0.500 in, Temperature 842 °F	0.2% offset
	510 MPa	74000 psi	
	@Diameter 12.7 mm, Temperature 25.0 °C	@Diameter 0.500 in, Temperature 77.0 °F	0.2% offset
Elongation at Break	40.4 %	40.4 %	
	@Diameter <=12.7 mm, Temperature 25.0 °C	@Diameter <=0.500 in, Temperature 77.0 °F	
	43.9 %	43.9 %	
	@Diameter <=12.7 mm, Temperature 450 °C	@Diameter <=0.500 in, Temperature 842 °F	
Modulus of Elasticity	162 GPa	23500 ksi	
	@Temperature 649 °C	@Temperature 1200 °F	
	171 GPa	24800 ksi	
	@Temperature 538 °C	@Temperature 1000 °F	
	177 GPa	25700 ksi	
	@Temperature 427 °C	@Temperature 801 °F	
	190 GPa	27600 ksi	
	@Temperature 316 °C	@Temperature 601 °F	
	207 GPa	30000 ksi	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Charpy Impact	45.0 J	33.2 ft-lb	
	@Temperature -196 °C	@Temperature -321 °F	Metal Sample from Plate Weld
	71.0 J	52.4 ft-lb	
	@Temperature 25.0 °C	@Temperature 77.0 °F	Metal Sample from Plate Weld

Thermal Properties	Metric	English	Comments
	12.4 Åµm/m-°C	6.89 Åµin/in-°F	

CTE, linear Thermal Properties	Metric @Temperature 25.0 - 200 °C	English @Temperature 77.0 - 392 °F	Comments
	12.4 Åµm/m-Å°C	6.89 Åµin/in-Å°F	
	@Temperature 25.0 - 100 °C	@Temperature 77.0 - 212 °F	
	12.6 Åµm/m-Å°C	7.00 Åµin/in-Å°F	
	@Temperature 25.0 - 300 °C	@Temperature 77.0 - 572 °F	
	12.9 Åµm/m-Å°C	7.17 Åµin/in-Å°F	
	@Temperature 25.0 - 400 °C	@Temperature 77.0 - 752 °F	
	13.2 Åµm/m-Å°C	7.33 Åµin/in-Å°F	
	@Temperature 25.0 - 500 °C	@Temperature 77.0 - 932 °F	
	13.3 Åµm/m-Å°C	7.39 Åµin/in-Å°F	
	@Temperature 25.0 - 600 °C	@Temperature 77.0 - 1110 °F	
Specific Heat Capacity	0.428 J/g-Å°C	0.102 BTU/lb-Å°F	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
	0.434 J/g-Å°C	0.104 BTU/lb-Å°F	
	@Temperature 100 °C	@Temperature 212 °F	
	0.443 J/g-Å°C	0.106 BTU/lb-Å°F	
	@Temperature 200 °C	@Temperature 392 °F	
	0.455 J/g-Å°C	0.109 BTU/lb-Å°F	
	@Temperature 300 °C	@Temperature 572 °F	
	0.468 J/g-Å°C	0.112 BTU/lb-Å°F	
	@Temperature 400 °C	@Temperature 752 °F	
	0.486 J/g-Å°C	0.116 BTU/lb-Å°F	
	@Temperature 500 °C	@Temperature 932 °F	
	0.536 J/g-Å°C	0.128 BTU/lb-Å°F	
	@Temperature 600 °C	@Temperature 1110 °F	
Thermal Conductivity	9.10 W/m-K @Temperature 25.0 °C	63.2 BTU-in/hr-ftÅ²- Å°F @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
	10.8 W/m-K	75.0 BTU-in/hr-ft ² - °F	
	@Temperature 100 °C	@Temperature 212 °F	
	12.6 W/m-K	87.4 BTU-in/hr-ft ² - °F	
	@Temperature 200 °C	@Temperature 392 °F	
	14.1 W/m-K	97.9 BTU-in/hr-ft ² - °F	
	@Temperature 300 °C	@Temperature 572 °F	
	16.1 W/m-K	112 BTU-in/hr-ft ² -°F	
	@Temperature 400 °C	@Temperature 752 °F	
	18.0 W/m-K	125 BTU-in/hr-ft ² -°F	
	@Temperature 500 °C	@Temperature 932 °F	
	21.6 W/m-K	150 BTU-in/hr-ft ² -°F	
	@Temperature 600 °C	@Temperature 1110 °F	
Melting Point	1328 - 1358 °C	2422 - 2476 °F	
Solidus	1328 °C	2422 °F	
Liquidus	1358 °C	2476 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	<= 0.50 %	<= 0.50 %	
Carbon, C	<= 0.010 %	<= 0.010 %	
Chromium, Cr	23 %	23 %	
Copper, Cu	1.6 %	1.6 %	
Iron, Fe	<= 3.0 %	<= 3.0 %	
Manganese, Mn	<= 0.50 %	<= 0.50 %	
Molybdenum, Mo	16 %	16 %	
Nickel, Ni	>= 57 %	>= 57 %	as balance
Silicon, Si	<= 0.080 %	<= 0.080 %	

Electrical Properties	Metric	English	Comments

Electrical Properties Electrical Resistivity	Metric @Temperature 25.0 Â°C	English 0.000128 ohm-cm	Comments
	0.000129 ohm-cm @Temperature 100 Â°C	0.000129 ohm-cm @Temperature 212 Â°F	
	0.000130 ohm-cm @Temperature 200 Â°C	0.000130 ohm-cm @Temperature 392 Â°F	
	0.000131 ohm-cm @Temperature 300 Â°C	0.000131 ohm-cm @Temperature 572 Â°F	
	0.000132 ohm-cm @Temperature 400 Â°C	0.000132 ohm-cm @Temperature 752 Â°F	
	0.000134 ohm-cm @Temperature 500 Â°C	0.000134 ohm-cm @Temperature 932 Â°F	
	0.000135 ohm-cm @Temperature 600 Â°C	0.000135 ohm-cm @Temperature 1110 Â°F	

Processing Properties	Metric	English	Comments
Annealing Temperature	1135 - 1150 Â°C	2075 - 2100 Â°F	followed by rapid air-cooling or water quenching

Descriptive Properties	Value	Comments
Thermal Diffusivity (cm ² /s)	at 100Â°C	
	at 200Â°C	
	at 25Â°C	
	at 300Â°C	
	at 400Â°C	
	at 500Â°C	
	at 600Â°C	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : [lookpolymers](#)

Address : United North Road 215,Fengxian District, Shanghai City,China