

Haynes Hastelloy® C-22HS Nickel Alloy Plate and Bar, Hot-rolled, Solution Annealed

Category : Metal , Nonferrous Metal , Nickel Alloy

Material Notes:

Outstanding Corrosion Resistance, High Strength HASTELLOY® C-22HSTM alloy is corrosion-resistant, nickel-chromium-molybdenum alloy which can be heat treated to obtain a strength approximately double that of other C-type alloys. Importantly, the corrosion resistance and ductility of the alloy remain excellent when in the high strength condition. In addition to its high uniform corrosion resistance in oxidizing as well as reducing environments, the as-heat treated C-22HS alloy possesses high resistance to chloride-induced pitting and crevice corrosion attack.C-22HS alloy is available in the form of plate, sheet, strip, billet, bar, wire, pipe, and tube. Heat Treatment: The high strength of C-22HS alloy is derived from the formation of strengthening particles of Ni₂(Mo,Cr) which form during the patented two-step age-hardening heat treatment. The approximately 48 hour heat treatment, 1300°F (705°C) FC to 1125°F (605°C)/32 hours/AC, is described in more detail on page 14. Solution Annealed and Filler Wire Applications: C-22HS alloy may also be considered for applications which do not require the high strength imparted by the heat treatment. In the annealed condition, C-22HS alloy has even higher corrosion-resistance, particularly with regard to localized corrosive attack. This localized attack resistance also makes the alloy an attractive candidate as a general-purpose filler metal or weld overlay. Applications: Agitators and blenders Shafting Fan blades and hubs Fasteners Springs Valves Dies Screws Wellhead parts Rings and gaskets Heat Treatment: Wrought forms of C-22HS alloy are furnished in the solution annealed condition, unless otherwise specified. The standard solution annealing treatment consists of heating to 1975°F (1080°C) followed by rapid air-cooling or water quenching. Parts which have been hot formed should be solution annealed prior to final fabrication or installation. To use the alloy in the high-strength condition, it is necessary to age-harden using a two step treatment of 1300°F (705°C) for 16 hours, furnace cooling to 1125°F (605°C) and holding at that temperature for 32 hours, followed by an air cool. Cold or hot-worked structures should normally be given a full solution anneal prior to performing the age-hardening treatment. Forming: C-22HS alloy has excellent forming characteristics, and cold forming is the preferred method of shaping. The alloy can be easily cold worked due to its good ductility. The alloy is generally stiffer than the austenitic stainless steels; therefore more energy is required during cold forming. For further information on the fabrication of C-type alloys, please consult publication H-2010. Machining: C-22HS alloy may be machined in either the solution annealed or age-hardened condition. Carbide or ceramic tools are recommended. For use in the age-hardened condition, it is suggested to rough machine in the annealed condition. After performing the age-hardening heat treatment, light machining may be performed to achieve desired final dimensions.Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Haynes-Hastelloy-C-22HS-Nickel-Alloy-Plate-and-Bar-Hot-rolled-Solution-Annealed.php

Physical Properties	Metric	English	Comments
Density	8.60 g/cc	0.311 lb/in ³	annealed
	8.64 g/cc	0.312 lb/in ³	age-hardened

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell B	88	88	Mill-annealed Bar
	92	92	Mill-annealed Plate

Mechanical Properties	Metric MPa	9110 psi English	Comments
Tensile Strength, Ultimate			
	@Temperature 600 °C	@Temperature 1110 °F	
	652 MPa	94600 psi	
	@Temperature 500 °C	@Temperature 932 °F	
	677 MPa	98200 psi	
	@Temperature 400 °C	@Temperature 752 °F	
	695 MPa	101000 psi	
	@Temperature 300 °C	@Temperature 572 °F	
	721 MPa	105000 psi	
	@Temperature 200 °C	@Temperature 392 °F	
	767 MPa	111000 psi	
	@Temperature 100 °C	@Temperature 212 °F	
	806 MPa	117000 psi	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Tensile Strength, Yield			
	223 MPa	32300 psi	
	@Strain 0.200 %, Temperature 600 °C	@Strain 0.200 %, Temperature 1110 °F	
	241 MPa	35000 psi	
	@Strain 0.200 %, Temperature 500 °C	@Strain 0.200 %, Temperature 932 °F	
	255 MPa	37000 psi	
	@Strain 0.200 %, Temperature 400 °C	@Strain 0.200 %, Temperature 752 °F	
	263 MPa	38100 psi	
	@Strain 0.200 %, Temperature 300 °C	@Strain 0.200 %, Temperature 572 °F	
	288 MPa	41800 psi	
	@Strain 0.200 %, Temperature 200 °C	@Strain 0.200 %, Temperature 392 °F	
	329 MPa	47700 psi	
	@Strain 0.200 %, Temperature 100 °C	@Strain 0.200 %, Temperature 212 °F	
	376 MPa	54500 psi	

Mechanical Properties	@Strain 0.200 %, Metric Temperature 25.0 °C	@Strain 0.200 %, English Temperature 77.0 °F	Comments
Elongation at Break	62.3 % @Temperature 25.0 °C	62.3 % @Temperature 77.0 °F	
	65.9 % @Temperature 200 °C	65.9 % @Temperature 392 °F	
	66.7 % @Temperature 100 °C	66.7 % @Temperature 212 °F	
	68.8 % @Temperature 300 °C	68.8 % @Temperature 572 °F	
	69.3 % @Temperature 500 °C	69.3 % @Temperature 932 °F	
	69.5 % @Temperature 400 °C	69.5 % @Temperature 752 °F	
	70.6 % @Temperature 600 °C	70.6 % @Temperature 1110 °F	
Reduction of Area	69.1 % @Temperature 600 °C	69.1 % @Temperature 1110 °F	
	70.9 % @Temperature 500 °C	70.9 % @Temperature 932 °F	
	73 % @Temperature 400 °C	73 % @Temperature 752 °F	
	75.2 % @Temperature 300 °C	75.2 % @Temperature 572 °F	
	77.3 % @Temperature 200 °C	77.3 % @Temperature 392 °F	
	77.5 % @Temperature 25.0 °C	77.5 % @Temperature 77.0 °F	
	78 % @Temperature 100 °C	78 % @Temperature 212 °F	

Mechanical Properties	Metric 181 GPa	English ksi	Comments
Modulus of Elasticity	@Temperature 600 °C	@Temperature 1110 °F	Dynamic
	195 GPa	28300 ksi	Dynamic
	@Temperature 500 °C	@Temperature 932 °F	
	205 GPa	29700 ksi	Dynamic
	@Temperature 400 °C	@Temperature 752 °F	
	209 GPa	30300 ksi	Dynamic
	@Temperature 300 °C	@Temperature 572 °F	
	211 GPa	30600 ksi	Dynamic
	@Temperature 200 °C	@Temperature 392 °F	
	218 GPa	31600 ksi	Dynamic
	@Temperature 100 °C	@Temperature 212 °F	
	223 GPa	32300 ksi	Dynamic
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	11.6 Åµm/m-°C	6.44 Åµin/in-°F	
	@Temperature 25.0 - 100 °C	@Temperature 77.0 - 212 °F	
	12.0 Åµm/m-°C	6.67 Åµin/in-°F	
	@Temperature 25.0 - 200 °C	@Temperature 77.0 - 392 °F	
	12.4 Åµm/m-°C	6.89 Åµin/in-°F	
	@Temperature 25.0 - 300 °C	@Temperature 77.0 - 572 °F	
	12.7 Åµm/m-°C	7.06 Åµin/in-°F	
	@Temperature 25.0 - 400 °C	@Temperature 77.0 - 752 °F	
	13.1 Åµm/m-°C	7.28 Åµin/in-°F	
	@Temperature 25.0 - 500 °C	@Temperature 77.0 - 932 °F	
	13.3 Åµm/m-°C	7.39 Åµin/in-°F	
	@Temperature 25.0 -	@Temperature 77.0 -	

Thermal Properties	600 °C Metric	1110 °F English	Comments
Specific Heat Capacity	0.412 J/g-°C @Temperature 25.0 °C	0.0985 BTU/lb-°F @Temperature 77.0 °F	
	0.434 J/g-°C @Temperature 100 °C	0.104 BTU/lb-°F @Temperature 212 °F	
	0.451 J/g-°C @Temperature 200 °C	0.108 BTU/lb-°F @Temperature 392 °F	
	0.465 J/g-°C @Temperature 300 °C	0.111 BTU/lb-°F @Temperature 572 °F	
	0.477 J/g-°C @Temperature 400 °C	0.114 BTU/lb-°F @Temperature 752 °F	
	0.488 J/g-°C @Temperature 500 °C	0.117 BTU/lb-°F @Temperature 932 °F	
	0.504 J/g-°C @Temperature 600 °C	0.120 BTU/lb-°F @Temperature 1110 °F	
Thermal Conductivity	11.8 W/m-K @Temperature 25.0 °C	81.9 BTU-in/hr-ft²-°F @Temperature 77.0 °F	
	13.5 W/m-K @Temperature 100 °C	93.7 BTU-in/hr-ft²-°F @Temperature 212 °F	
	15.4 W/m-K @Temperature 200 °C	107 BTU-in/hr-ft²-°F @Temperature 392 °F	
	17.1 W/m-K @Temperature 300 °C	119 BTU-in/hr-ft²-°F @Temperature 572 °F	
	18.6 W/m-K @Temperature 400 °C	129 BTU-in/hr-ft²-°F @Temperature 752 °F	
	20.5 W/m-K @Temperature 500 °C	142 BTU-in/hr-ft²-°F @Temperature 932 °F	
	22.4 W/m-K @Temperature 600 °C	155 BTU-in/hr-ft²-°F @Temperature 1110 °F	

Thermal Properties	Metric	English	Comments
Solidus	1304 °C	2379 °F	
Liquidus	1368 °C	2494 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000980 ohm-cm @Temperature 25.0 °C	0.0000980 ohm-cm @Temperature 77.0 °F	
	0.000100 ohm-cm @Temperature 100 °C	0.000100 ohm-cm @Temperature 212 °F	
	0.000104 ohm-cm @Temperature 200 °C	0.000104 ohm-cm @Temperature 392 °F	
	0.000108 ohm-cm @Temperature 300 °C	0.000108 ohm-cm @Temperature 572 °F	
	0.000112 ohm-cm @Temperature 400 °C	0.000112 ohm-cm @Temperature 752 °F	
	0.000115 ohm-cm @Temperature 500 °C	0.000115 ohm-cm @Temperature 932 °F	
	0.000117 ohm-cm @Temperature 600 °C	0.000117 ohm-cm @Temperature 1110 °F	

Processing Properties	Metric	English	Comments
Annealing Temperature	1079 °C	1975 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China