

Haynes Hastelloy® W alloy, gas metal arc welds, as-welded

Category : Metal , Nonferrous Metal , Nickel Alloy , Superalloy

Material Notes:

Solid solution-strengthened developed as a filler metal for welding of dissimilar alloys. Applications include excellent dissimilar welding characteristics in the gas turbine, aerospace, and chemical process industries. Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Haynes-Hastelloy-W-alloy-gas-metal-arc-welds-as-welded.php

Physical Properties	Metric	English	Comments
Density	9.00 g/cc	0.325 lb/in ³	at RT

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	870 MPa	126000 psi	
	310 MPa	45000 psi	
	@Temperature 870 Â°C	@Temperature 1600 Â°F	
Tensile Strength, Yield	555 MPa	80500 psi	
	285 MPa	41300 psi	
	@Temperature 870 Â°C	@Temperature 1600 Â°F	
Elongation at Break	38 %	38 %	
	41 %	41 %	
	@Temperature 870 Â°C	@Temperature 1600 Â°F	
Reduction of Area	32 %	32 %	
	42 %	42 %	
	@Temperature 870 Â°C	@Temperature 1600 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear	13.2 Âµm/m-Â°C	7.33 Âµin/in-Â°F	
	@Temperature 20.0 - 600 Â°C	@Temperature 68.0 - 1110 Â°F	
	13.2 Âµm/m-Â°C	7.33 Âµin/in-Â°F	
	@Temperature 20.0 - 500 Â°C	@Temperature 68.0 - 932 Â°F	

Thermal Properties	Metric	English	Comments
	@Temperature 20.0 - 700 Â°C	@Temperature 68.0 - 1290 Â°F	
	14.2 Âµm/m-Â°C	7.89 Âµin/in-Â°F	
	@Temperature 20.0 - 800 Â°C	@Temperature 68.0 - 1470 Â°F	
	14.8 Âµm/m-Â°C	8.22 Âµin/in-Â°F	
	@Temperature 20.0 - 900 Â°C	@Temperature 68.0 - 1650 Â°F	
	15.3 Âµm/m-Â°C	8.50 Âµin/in-Â°F	
	@Temperature 20.0 - 1000 Â°C	@Temperature 68.0 - 1830 Â°F	

Component Elements Properties	Metric	English	Comments
Carbon, C	<= 0.12 %	<= 0.12 %	
Chromium, Cr	5.0 %	5.0 %	
Cobalt, Co	2.5 %	2.5 %	
Iron, Fe	6.0 %	6.0 %	
Manganese, Mn	<= 1.0 %	<= 1.0 %	
Molybdenum, Mo	24 %	24 %	
Nickel, Ni	63 %	63 %	
Silicon, Si	<= 1.0 %	<= 1.0 %	
Vanadium, V	<= 0.60 %	<= 0.60 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China