

Haynes Ultimet® alloy, aged 1000 hours at 982°C

Category : Metal , Nonferrous Metal , Cobalt Alloy , Superalloy

Material Notes:

Co content as balance, excellent corrosion resistance, outstanding wear resistance, high tensile strength combined with excellent impact toughness and ductility. Ideal welding material with exceptional ductility and resistance to weld cracking, very easy to apply as an overlay, multiple layers applicable with little to no preheat. Applications include agitators, blenders, bolts, dies, extruders, fan blades, filters, glass plungers, nozzles, pumps, rolls, screw conveyors, and valve parts. Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Haynes-Ultimet-alloy-aged-1000-hours-at-982C.php

Physical Properties	Metric	English	Comments
Density	8.47 g/cc	0.306 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	1000 MPa	145000 psi	
Tensile Strength, Yield	490 MPa @Strain 0.200 %	71100 psi @Strain 0.200 %	
Elongation at Break	41 %	41 %	in 50.8 mm
Modulus of Elasticity	180 GPa @Temperature 649 °C	26100 ksi @Temperature 1200 °F	(heat treated at 1121°C (2050°F), water quenched plate)
	189 GPa @Temperature 538 °C	27400 ksi @Temperature 1000 °F	(heat treated at 1121°C (2050°F), water quenched plate)
	197 GPa @Temperature 427 °C	28600 ksi @Temperature 801 °F	(heat treated at 1121°C (2050°F), water quenched plate)
	206 GPa @Temperature 316 °C	29900 ksi @Temperature 601 °F	(heat treated at 1121°C (2050°F), water quenched plate)
	215 GPa @Temperature 204 °C	31200 ksi @Temperature 399 °F	(heat treated at 1121°C (2050°F), water quenched plate)
Charpy Impact	60.0 J @Temperature 23.0 °C	44.3 ft-lb @Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
CTE, linear	@Temperature 26.0 - 316 Â°C	@Temperature 78.8 - 601 Â°F	
	14.5 Âµm/m-Â°C	8.06 Âµin/in-Â°F	
	@Temperature 26.0 - 427 Â°C	@Temperature 78.8 - 801 Â°F	
	14.8 Âµm/m-Â°C	8.22 Âµin/in-Â°F	
	@Temperature 26.0 - 538 Â°C	@Temperature 78.8 - 1000 Â°F	
	15.1 Âµm/m-Â°C	8.39 Âµin/in-Â°F	
	@Temperature 26.0 - 649 Â°C	@Temperature 78.8 - 1200 Â°F	
	15.9 Âµm/m-Â°C	8.83 Âµin/in-Â°F	
Specific Heat Capacity	@Temperature 26.0 - 760 Â°C	@Temperature 78.8 - 1400 Â°F	
	16.4 Âµm/m-Â°C	9.11 Âµin/in-Â°F	
	@Temperature 26.0 - 871 Â°C	@Temperature 78.8 - 1600 Â°F	
	16.9 Âµm/m-Â°C	9.39 Âµin/in-Â°F	
	@Temperature 26.0 - 982 Â°C	@Temperature 78.8 - 1800 Â°F	
	0.456 J/g-Â°C	0.109 BTU/lb-Â°F	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
	0.470 J/g-Â°C	0.112 BTU/lb-Â°F	
	@Temperature 100 Â°C	@Temperature 212 Â°F	
	0.482 J/g-Â°C	0.115 BTU/lb-Â°F	
	@Temperature 200 Â°C	@Temperature 392 Â°F	
	0.504 J/g-Â°C	0.120 BTU/lb-Â°F	
	@Temperature 300 Â°C	@Temperature 572 Â°F	
	0.525 J/g-Â°C	0.125 BTU/lb-Â°F	
	@Temperature 400 Â°C	@Temperature 752 Â°F	
	0.545 J/g-Â°C	0.130 BTU/lb-Â°F	
	@Temperature 500 Â°C	@Temperature 932 Â°F	
	0.573 J/g-Â°C	0.137 BTU/lb-Â°F	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	12.3 W/m-K	85.4 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
	13.8 W/m-K	95.8 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 100 Â°C	@Temperature 212 Â°F	
	15.6 W/m-K	108 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 200 Â°C	@Temperature 392 Â°F	
	17.5 W/m-K	121 BTU-in/hr-ftÂ²-Â°F	
Melting Point	@Temperature 300 Â°C	@Temperature 572 Â°F	
	19.4 W/m-K	135 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 400 Â°C	@Temperature 752 Â°F	
	21.5 W/m-K	149 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 500 Â°C	@Temperature 932 Â°F	
	23.9 W/m-K	166 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 600 Â°C	@Temperature 1110 Â°F	
Solidus	1332 - 1354 Â°C	2430 - 2469 Â°F	
Liquidus	1332 Â°C	2430 Â°F	
	1354 Â°C	2469 Â°F	

Component Elements Properties	Metric	English	Comments
Carbon, C	0.060 %	0.060 %	
Chromium, Cr	26 %	26 %	
Cobalt, Co	54 %	54 %	
Iron, Fe	3.0 %	3.0 %	
Manganese, Mn	0.80 %	0.80 %	
Molybdenum, Mo	5.0 %	5.0 %	
Nickel, Ni	9.0 %	9.0 %	
Nitrogen, N	0.080 %	0.080 %	

Silicon, Si Component Elements Properties	0.30 % Metric	0.30 % English	Comments
Tungsten, W	2.0 %	2.0 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000870 ohm-cm	0.0000870 ohm-cm	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
	0.0000890 ohm-cm	0.0000890 ohm-cm	
	@Temperature 100 Â°C	@Temperature 212 Â°F	
	0.0000930 ohm-cm	0.0000930 ohm-cm	
	@Temperature 200 Â°C	@Temperature 392 Â°F	
	0.0000960 ohm-cm	0.0000960 ohm-cm	
	@Temperature 300 Â°C	@Temperature 572 Â°F	
	0.000100 ohm-cm	0.000100 ohm-cm	
	@Temperature 400 Â°C	@Temperature 752 Â°F	
	0.000103 ohm-cm	0.000103 ohm-cm	
	@Temperature 500 Â°C	@Temperature 932 Â°F	
	0.000105 ohm-cm	0.000105 ohm-cm	
	@Temperature 600 Â°C	@Temperature 1110 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China