

Hexcel® HexPly® 8551-7 Epoxy Matrix, Carbon Tape Form

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

Material Notes:

Information provided by HexCel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexPly-8551-7-Epoxy-Matrix-Carbon-Tape-Form.php

Physical Properties	Metric	English	Comments
Volatiles	<= 1.0 %	<= 1.0 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	93.3 °C	200 °F	Epoxy Matrix Limit

Processing Properties	Metric	English	Comments
Shelf Life	4.00 Month	4.00 Month	
	@Temperature 4.00 °C	@Temperature 39.2 °F	
	12.0 Month	12.0 Month	
	@Temperature -18.0 °C	@Temperature -0.400 °F	

Descriptive Properties	Value	Comments
Dry Resin Content (%)	34-40	
Fiber Volume (%)	60	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China