

Hexcel® HexPly® 8552 Epoxy Matrix, Carbon Tape Form

Category : Polymer , Thermoset , Carbon Fiber/Thermoset Composite , Epoxy , Epoxy/Carbon Fiber Composite

Material Notes:

Information provided by HexCel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexPly-8552-Epoxy-Matrix-Carbon-Tape-Form.php

Physical Properties	Metric	English	Comments
Volatiles	<= 1.0 %	<= 1.0 %	Prepreg

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	121 °C	250 °F	Epoxy Matrix Limit

Processing Properties	Metric	English	Comments
Gel Time	12.0 - 22.0 min	12.0 - 22.0 min	Prepreg

Descriptive Properties	Value	Comments
Dry Resin Content (%)	34-38	Prepreg
Fiber Volume (%)	60	Laminate
Flow (%)	10-22	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China