

Hexcel® HexPly® 954-2A Curing Cyanate Resin, K1100 Fiber

Category : Polymer , Thermoset , Epoxy

Material Notes:

Information provided by HexCel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexPly-954-2A-Curing-Cyanate-Resin-K1100-Fiber.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	1213 MPa	175900 psi	0°
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tensile Modulus	558 GPa	80900 ksi	0°
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Flexural Yield Strength	476 MPa	69000 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Flexural Modulus	427 GPa	61900 ksi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Compressive Yield Strength	262 MPa	38000 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Compressive Modulus	558 GPa	80900 ksi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Shear Strength	24.0 MPa	3480 psi	0°
	@Temperature 22.0 °C	@Temperature 71.6 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China