

Hexcel® HexPly® 954-3A Curing Cyanate Resin, M60J Fiber

Category : Polymer , Thermoset , Epoxy

Material Notes:

Information provided by HexCel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexPly-954-3A-Curing-Cyanate-Resin-M60J-Fiber.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	2120 MPa	307000 psi	0°
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tensile Modulus	391 GPa	56700 ksi	0°
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Flexural Yield Strength	858 MPa	124000 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Flexural Modulus	274 GPa	39700 ksi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Compressive Yield Strength	827 MPa	120000 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Compressive Modulus	333 GPa	48300 ksi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Shear Modulus	3.70 GPa	537 ksi	In-Plane
Shear Strength	45.0 MPa	6530 psi	In-Plane

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China