

Hexcel® HexPly® EH04 Epoxy Resin System, AS4C Fiber

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

Material Notes:

AS4C 150 24" EH04 35%; Normalized to 55% fiber volume; 75°F, dryInformation provided by HexCel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexPly-EH04-Epoxy-Resin-System-AS4C-Fiber.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	2320 MPa	336000 psi	
Tensile Modulus	125 GPa	18100 ksi	
Flexural Yield Strength	1320 MPa	191000 psi	
Flexural Modulus	117 GPa	16900 ksi	
Compressive Yield Strength	1500 MPa	218000 psi	
Compressive Modulus	117 GPa	16900 ksi	
Shear Strength	84.1 MPa	12200 psi	Short Beam

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China