

Hexcel® HexPly® EH04 Epoxy Resin System, M35J Fiber

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

Material Notes:

MS35J 120 24" EH04 31%; Normalized to 55% fiber volume; 75°F, dryInformation provided by HexCel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexPly-EH04-Epoxy-Resin-System-M35J-Fiber.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	2600 MPa	377000 psi	
Tensile Modulus	183 GPa	26500 ksi	
Flexural Yield Strength	1570 MPa	228000 psi	
Flexural Modulus	205 GPa	29700 ksi	
Compressive Yield Strength	1510 MPa	219000 psi	
Compressive Modulus	164 GPa	23800 ksi	
Shear Strength	84.1 MPa	12200 psi	Short Beam

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China