

## Hexcel® HexWeb® CFC™ -20-1/8-11.0 Composite Flooring Honeycomb Core

Category : Other Engineering Material , Composite Core Material , Polymer , Thermoset , Aramid

### Material Notes:

Hexweb® CFC™ -20 is manufactured from NOMEX aramid fiber sheets. A thermosetting adhesive is used to bond these sheets at the nodes and, after expanding to the hexagonal configuration, the block is dipped in phenolic resin. After curing the resin, slices are cut to the desired thickness. Features: Specifically designed for aircraft flooring applications; Superior properties and performance over balsa and foam core materials; Proven durability in extensive flooring tests; Significant weight advantage over balsa and foam core materials; Exceeds all FAA safety requirements; Excellent property retention at 350°F; Moisture and fungus resistant. Applications: Hexweb® CFC™ -20 honeycomb core was specifically developed to provide a tough, lightweight core material for use in aircraft flooring systems. A range of product densities are available to fit a wide variety of loading requirements. The core material when bonded to metallic or nonmetallic facings provides a flooring panel sheet which may be cut or contoured to fit any aircraft flooring module.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Hexcel-HexWeb-CFC-20-18-110-Composite-Flooring-Honeycomb-Core.php](http://www.lookpolymers.com/polymer_Hexcel-HexWeb-CFC-20-18-110-Composite-Flooring-Honeycomb-Core.php)

Physical Properties	Metric	English	Comments
Density	0.176 g/cc	0.00637 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	>= 15.2 MPa	>= 2200 psi	Bare, min
	>= 15.9 MPa	>= 2300 psi	Stabilized, min
	17.9 MPa	2600 psi	Bare, typ
	18.6 MPa	2700 psi	Stabilized, typ
Shear Modulus	0.110 GPa	16.0 ksi	Plate Shear, W Direction, typ, preliminary value obtained from limited testing
	0.193 GPa	28.0 ksi	Plate Shear, L Direction, typ, preliminary value obtained from limited testing
Shear Strength	>= 2.48 MPa	>= 360 psi	Plate Shear, W Direction, min, preliminary value obtained from limited testing
	3.10 MPa	450 psi	Plate Shear, W Direction, typ, preliminary value obtained from limited testing
	>= 3.52 MPa	>= 510 psi	Plate Shear, L Direction, min, preliminary value obtained from limited testing
	4.41 MPa	640 psi	Plate Shear, L Direction, typ, preliminary value obtained from limited testing

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**