

Hexcel® HexWeb® CR-PAA™ 1/4-5052-0.002 Phosphoric Acid Anodized Aluminum Honeycomb

Category: Metal, Metal Foam, Mesh, or Honeycomb, Nonferrous Metal, Aluminum Alloy, 5000 Series Aluminum Alloy

Material Notes:

Grade is designated as "Cell Size-Alloy-Foil Gauge." The life cycle of aluminum honeycomb sandwich structures in a given application can be directly related to the quality of the bond between the face sheets that carry bending loads and the honeycomb that carries the shear loads. The adhesive is the interface between the facing and the core in the same way that the oxide on the aluminum and the primer that has been applied to it is the interface between the honeycomb substrate material and the bonding adhesive. This interface is critical to the performance of honeycomb bonded assemblies.HexWeb® CR-PAA™ is designed for aircraft structures that are exposed to demanding environmental conditions. HexWeb® CR-PAA™ outperforms standard MIL-C-7438 core in salt spray and HexWeb® crack propagation tests.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexWeb-CR-PAA-14-5052-0002-Phosphoric-Acid-Anodized-Aluminum-Honeycomb.php

Physical Properties	Metric	English	Comments
Density	0.0689 g/cc	0.00249 lb/in ³	Nominal

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	>= 2.41 MPa	>= 350 psi	Bare, min
	>= 2.55 MPa	>= 370 psi	Stabilized, min
	3.45 MPa	500 psi	Bare, typ
	3.72 MPa	540 psi	Stabilized, typ
Compressive Modulus	0.965 GPa	140 ksi	Stabilized, typ
Shear Modulus	0.205 GPa	29.8 ksi	Plate Shear, W Direction, typ
	0.455 GPa	66.0 ksi	Plate Shear, L Direction, typ
Shear Strength	>= 1.07 MPa	>= 155 psi	Plate Shear, W Direction, min
	1.38 MPa	200 psi	Plate Shear, W Direction, typ
	>= 1.83 MPa	>= 265 psi	Plate Shear, L Direction, min
	2.21 MPa	320 psi	Plate Shear, L Direction, typ

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842



Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China