

Hippe EP MP 21 Mica Paper Reinforced Epoxy Resin - Round, Rolled Tube

Category : Polymer , Thermoset , Epoxy , Epoxy, Molded, Mineral Filled

Material Notes:

Used in mechanical, electrical and electronic applications. Good stability of electrical properties when exposed to high relative humidity.

Good heat resistance. Information provided by Hippe.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hippe-EP-MP-21-Mica-Paper-Reinforced-Epoxy-Resin-Round-Rolled-Tube.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.50 - 1.80 g/cc	1.50 - 1.80 g/cc	IEC 1212-2 7.2

Mechanical Properties	Metric	English	Comments
Flexural Strength	>= 100 MPa @Diameter >=100 mm	>= 14500 psi @Diameter >=3.94 in	Perpendicular to laminations; IEC 1212-2 4.1
Compressive Strength	>= 60.0 MPa	>= 8700 psi	Axial; IEC 1212-2 4.2

Electrical Properties	Metric	English	Comments
Insulation Resistance	>= 1.00e+8 ohm @Diameter 8.00 - 10.0 mm	>= 1.00e+8 ohm @Diameter 0.315 - 0.394 in	After immersion in water; IEC 1212-2 5.2
Dielectric Constant	<= 5.2 @Frequency 1.00e+6 Hz	<= 5.2 @Frequency 1.00e+6 Hz	IEC 1212-2 5.3
Dielectric Breakdown	>= 30000 V @Temperature 90.0 °C, Time 20.0 sec	>= 30000 V @Temperature 194 °F, Time 0.00556 hour	Step -by-step test, In oil, parallel to laminations; IEC 1212-2 5.1
	>= 30000 V @Temperature 90.0 °C, Time 60.0 sec	>= 30000 V @Temperature 194 °F, Time 0.0167 hour	Proof test, In oil, parallel to laminations; IEC 1212-2 5.1
Dissipation Factor	<= 0.040 @Frequency 1.00e+6 Hz	<= 0.040 @Frequency 1.00e+6 Hz	IEC 1212-2 5.3

Descriptive Properties	Value	Comments
Cohesion between layers	> 30 MPa	IEC 1212-2 4.3, Internal diameter <100 mm
Thermal Endurance	155 T.I.	IEC 1212-2 7.1

Water Absorption Descriptive Properties	< 2 mg/cm ³ Value	IEC 1213-2 7.1 Comments
--	---------------------------------	----------------------------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China