

Honeywell ACLAR® 11A(0.60 mil) CTFE Homopolymer, Barrier Film (discontinued **)

Category : Polymer , Film , Thermoplastic , Fluoropolymer , Polychlorotrifluoroethylene (PCTFE); Molded

Material Notes:

Description: ACLAR® 11A is a CTFE homopolymer, high performance barrier film for industrial and electronics applications. Information provided by Honeywell.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Honeywell-ACLAR-11A060-mil-CTFE-Homopolymer-Barrier-Film-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.11 g/cc	2.11 g/cc	ASTM D1505
Density	2.10 g/cc	0.0760 lb/in ³	Yield Density
Water Vapor Transmission	0.420 g/m ² /day	0.0270 g/100 in ² /day	100°F (37.8°C) / 100%RH; ASTM F1249
Thickness	15.2 microns	0.600 mil	

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	70 - 130 %	70 - 130 %	ASTM D882
Film Elongation at Break, TD	200 - 300 %	200 - 300 %	ASTM D882
Secant Modulus, MD	1.207 - 1.551 GPa	175.1 - 225.0 ksi	ASTM D882
Secant Modulus, TD	1.172 - 1.413 GPa	170.0 - 204.9 ksi	ASTM D882
Tear Strength Test	275 - 325	275 - 325	graves tear TD, grams/mil; ASTM D1004
	350 - 400	350 - 400	graves tear MD, grams/mil; ASTM D1004
Film Tensile Strength at Break, MD	82.7 - 138 MPa	12000 - 20000 psi	ASTM D882
Film Tensile Strength at Break, TD	41.4 - 62.1 MPa	6000 - 9000 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.209 W/m-K	1.45 BTU-in/hr-ft ² -°F	
Melting Point	211 °C	412 °F	crystalline melting point; ASTM D4591
Oxygen Index	100 %	100 %	ASTM D2863
Shrinkage, MD	8.0 - 15 %	8.0 - 15 %	300°F / 149°C - 10 min.; ASTM D1204

Shrinkage, TD	-13.0 - -8.00 %	-13.0 - -8.00 %	300°F / 149°C - 10 min.; ASTM D1204
Thermal Properties	Metric	English	Comments

Optical Properties	Metric	English	Comments
Haze	<= 1.0 %	<= 1.0 %	ASTM D1003

Descriptive Properties	Value	Comments
Flammability	non flammable	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China