

## Huntsman DY 9577 Epoxy Accelerator

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

### Material Notes:

Mix Ratio with GY 6010 is 1. Comments/Applications: Casting, encapsulation, powder coatings, filament windings, pultrusion, molding, electrical tapes. Can be used as a catalyst. Latent at RT in GY 6010. BCL3 amine complex. Yellowish brown semi-solid. High reactivity above 120°C. Good working time below 80°C. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Huntsman-DY-9577-Epoxy-Accelerator.php](http://www.lookpolymers.com/polymer_Huntsman-DY-9577-Epoxy-Accelerator.php)

| Physical Properties | Metric     | English    | Comments |
|---------------------|------------|------------|----------|
| Viscosity           | 26 - 35 cP | 26 - 35 cP |          |

| Processing Properties  | Metric | English | Comments  |
|------------------------|--------|---------|---|
| Processing Temperature | 120 °C | 248 °F  | Cure Schedule: 2 hrs @ 120°C, 6 hrs @ 150°C, or 2 hrs @ 190°C |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China