

## Huntsman HT 3380-1 Special Hardener

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

### Material Notes:

Mix Ratio with GT 7013 is 18. Comments/Applications: Acid-anhydride functional crosslinker useful in FDA powder and can coating applications. \*Mix ratio with GT 7013. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Huntsman-HT-3380-1-Special-Hardener.php](http://www.lookpolymers.com/polymer_Huntsman-HT-3380-1-Special-Hardener.php)

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	95.0 - 110 Â°C	203 - 230 Â°F	Softening Range

Processing Properties	Metric	English	Comments
Processing Temperature	170 Â°C	338 Â°F	Cure Schedule: 5/20 min @ 170/220Â°C

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China