

## Huntsman HY 3440 Phenalkamine Hardener

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

### Material Notes:

Approx. H+ equivalent weight 80. Mix Ratio with GY 6010 is 30. Comments/Applications: Low temperature cure coatings with excellent corrosion and moisture resistance. Cure can go down to 0°C. For use in maintenance and marine coatings. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Huntsman-HY-3440-Phenalkamine-Hardener.php](http://www.lookpolymers.com/polymer_Huntsman-HY-3440-Phenalkamine-Hardener.php)

Processing Properties	Metric	English	Comments
Processing Temperature	25.0 °C	77.0 °F	Cure Schedule: 7 days @ 25°C

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China