

Huntsman HY 825 US Polyamide

Category : Polymer , Thermoset , Epoxy

Material Notes:

Approx. H+ equivalent weight 100. Mix Ratio with GY 6010 is 81. Comments/Applications: Solvent free, moderate molecular weight and amine content. Good adhesion, tough. Adhesives, casting, caulking, potting, sealants and coatings. Flexible mix ratio range. Usually used with "Type 1" epoxy resins. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-HY-825-US-Polyamide.php

Physical Properties	Metric	English	Comments
Viscosity	8000 - 12000 cP	8000 - 12000 cP	

Processing Properties	Metric	English	Comments
Pot Life	390 min	390 min	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China