

Huntsman HY 840 US Polyamide

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy Adhesive

Material Notes:

Approx. H+ equivalent weight 130. Mix Ratio with GY 6010 is 81. Comments/Applications: Solvent free, low viscosity, high amine content with higher flexibility and toughness. Flexible mix ratio 33 - 100 PHR, with GY 6010. High solids or solvent free industrial coatings, adhesives, general purpose industrial. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-HY-840-US-Polyamide.php

Physical Properties	Metric	English	Comments
Viscosity	3000 - 6000 cP	3000 - 6000 cP	

Processing Properties	Metric	English	Comments
Pot Life	210 min	210 min	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China