

Huntsman IROGRAN® A 85 P 4394 FCM Ether-Based TPU-For Food Contact

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Ether Grade

Material Notes:

Extrusion grade; High microbial resistance, high transparencyInformation provided by Huntsman

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-IROGRAN-A-85-P-4394-FCM-Ether-Based-TPU-For-Food-Contact.php

Physical Properties	Metric	English	Comments
Melt Flow	55 g/10 min	55 g/10 min	55 cm ³ /10 min; Melt Volume Rate

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85	85	
Hardness, Shore D	36	36	
Tensile Strength at Break	45.0 MPa	6530 psi	
Elongation at Break	640 %	640 %	
Tear Strength	60.0 kN/m	342 pli	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China