

Huntsman PE1068 Film Extrusion Polyethylene (discontinued **)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Film Grade

Material Notes:

Homopolymer and FDA compliant. Features: Exceptional draw down and processability even to 1/2 mil; excellent strength, good heat sealability, and good optical. FDA Notes: Conforms to FDA regulation 21 CFR 177.1520 (c)2.2 under condition of use B through H described in Table 2 of 21 CFR 176.170. Film properties based on 1.0 guage (25 µm) thickness; blow-up ratio 2:1. Information provided by Huntsman Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-PE1068-Film-Extrusion-Polyethylene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.922 g/cc	0.0333 lb/in ³	ASTM D1505
Thickness	25.4 microns	1.00 mil	
Melt Flow	5.5 g/10 min	5.5 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	52	52	ASTM D2240
Tensile Strength, Ultimate	10.0 MPa	1450 psi	ASTM D638
Tensile Strength, Yield	10.0 MPa	1450 psi	ASTM D638
Film Elongation at Break, MD	275 %	275 %	ASTM D882
Film Elongation at Break, TD	400 %	400 %	ASTM D882
Elongation at Break	400 %	400 %	ASTM D638
Modulus of Elasticity	0.242 GPa	35.1 ksi	Secant; ASTM D638
Secant Modulus, MD	0.159 GPa	23.1 ksi	ASTM D882
Secant Modulus, TD	0.186 GPa	27.0 ksi	ASTM D882
Dart Drop	1.77 g/micron	45.0 g/mil	ASTM D1709
Dart Drop Test	45.0 g	0.0992 lb	ASTM D1709
Film Tensile Strength at Break, MD	17.0 MPa	2470 psi	ASTM D882
Film Tensile Strength at Break, TD	14.0 MPa	2030 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Vicat Softening Point	96.0 °C	205 °F	ASTM D1525

Thermal Properties	Metric	English	Comments
Optical Properties	Metric	English	Comments
Haze	4.0 %	4.0 %	ASTM D1003
Gloss	78 %	78 %	at 45°; ASTM D523

Processing Properties	Metric	English	Comments
Melt Temperature	143 - 154 °C	289 - 309 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China