

Huntsman PE1403 EVA Film Extrusion (discontinued **)

Category : Polymer , Film , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Film Grade

Material Notes:

4% Vinyl Acetate EVA Copolymer, DMF listed and FDA compliant
Features: High clarity film with good toughness and flexibility at low temperatures.
Applications: Film extrusion: frozen food and general purpose for low temperature use.
FDA Notes: Conforms to FDA regulation 21 CFR 177.1350 under condition of use C through G described in Table 2 of 21 CFR 176.170
Film properties based on 1.0 guage (25 µm) thickness; blow-up ratio 2:1.
Information provided by Huntsman Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-PE1403-EVA-Film-Extrusion-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.928 g/cc	0.0335 lb/in ³	ASTM D1505
Thickness	25.4 microns	1.00 mil	
Melt Flow	1.3 g/10 min	1.3 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	47	47	ASTM D2240
Tensile Strength, Ultimate	16.0 MPa	2320 psi	ASTM D638
Tensile Strength, Yield	9.00 MPa	1310 psi	ASTM D638
Film Elongation at Break, MD	425 %	425 %	ASTM D882
Film Elongation at Break, TD	700 %	700 %	ASTM D882
Elongation at Break	800 %	800 %	ASTM D638
Modulus of Elasticity	0.235 GPa	34.1 ksi	Secant; ASTM D638
Secant Modulus, MD	0.128 GPa	18.6 ksi	ASTM D882
Secant Modulus, TD	0.159 GPa	23.1 ksi	ASTM D882
Dart Drop	6.69 g/micron	170 g/mil	ASTM D1709
Dart Drop Test	170 g	0.375 lb	ASTM D1709
Film Tensile Strength at Break, MD	24.0 MPa	3480 psi	ASTM D882
Film Tensile Strength at Break, TD	22.0 MPa	3190 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Vicat Softening Point	90.0 °C	194 °F	ASTM D1525

Thermal Properties	Metric	English	Comments
Optical Properties	Metric	English	Comments
Haze	5.0 %	5.0 %	ASTM D1003
Gloss	73 %	73 %	at 45°; ASTM D523

Processing Properties	Metric	English	Comments
Melt Temperature	182 - 193 °C	360 - 379 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China