

Huntsman PE1753 EVA Film Extrusion (discontinued **)

Category : Polymer , Film , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Film Grade

Material Notes:

7.5% Vinyl Acetate EVA copolymer and FDA compliant Features: Yields film with good clarity and excellent impact strength. Applications:

Film extrusion: icebags, liquid packaging, lamination film, and medical tubing. FDA Notes: Conforms to FDA regulation 21 CFR 177.1350

under condition of use C through G described in Table 2 of 21 CFR 176.170 Film properties based on 1.0 guage (25 µm) thickness; blow-up

ratio 2:1. Information provided by Huntsman Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-PE1753-EVA-Film-Extrusion-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.928 g/cc	0.0335 lb/in ³	ASTM D1505
Thickness	25.4 microns	1.00 mil	
Melt Flow	1.2 g/10 min	1.2 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	44	44	ASTM D2240
Tensile Strength, Ultimate	16.0 MPa	2320 psi	ASTM D638
Tensile Strength, Yield	8.00 MPa	1160 psi	ASTM D638
Film Elongation at Break, MD	250 %	250 %	ASTM D882
Film Elongation at Break, TD	400 %	400 %	ASTM D882
Elongation at Break	1000 %	1000 %	ASTM D638
Modulus of Elasticity	0.138 GPa	20.0 ksi	Secant; ASTM D638
Secant Modulus, MD	0.104 GPa	15.1 ksi	ASTM D882
Secant Modulus, TD	0.110 GPa	16.0 ksi	ASTM D882
Dart Drop	11.0 g/micron	280 g/mil	ASTM D1709
Dart Drop Test	280 g	0.617 lb	ASTM D1709
Film Tensile Strength at Break, MD	24.0 MPa	3480 psi	ASTM D882
Film Tensile Strength at Break, TD	22.0 MPa	3190 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Vicat Softening Point	79.0 °C	174 °F	ASTM D1525

Thermal Properties	Metric	English	Comments
Optical Properties	Metric	English	Comments
Haze	5.0 %	5.0 %	ASTM D1003
Gloss	70 %	70 %	at 45°; ASTM D523

Processing Properties	Metric	English	Comments
Melt Temperature	193 - 204 °C	379 - 399 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China