

Hybrid Plastics POSS® MA0719 Methacryllsooctyl-POSS®

Category: Other Engineering Material, Additive/Filler for Polymer, Polymer, Thermoplastic, Siloxane, Thermoset, Methacrylate

Material Notes:

POSS® Nanostructured Chemical Technology has two unique features: (1) the chemical composition is a hybrid, intermediate (RSiO1.5) between that of silica (SiO2) and silicones (R2SiO). (2) POSS® molecules are physically large ranging from approximately 1-3 nm. POSS® materials are thermally and chemically more robust than silicones and their nanostructured architecture imparts unique properties by controlling polymer chain motion at the molecular level. POSS®-Methacrylates possess a hybrid inorganic-organic three-dimensional structure, which contains from one to eight methacryl groups. The majority of POSS®-Methacrylates contain seven non-reactive organic groups and one methacryl group. While the monofunctional methacrylates can be incorporated into thermoplastics by copolymerization or grafting, the multifunctional methacrylates can be used as effective cross-linkers. They react similarly in polymerization, grafting and cross-linking reactions to standard organic monomers. While reacting similarly to simple organic methacrylates, POSS®-Methacrylates impart significant improvements in the thermal, mechanical, and gas separation properties of traditional plastics.Information provided by Hybrid Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hybrid-Plastics-POSS-MA0719-Methacryllsooctyl-POSS.php

| Physical Properties | Metric | English | Comments |
|---------------------|---------------|---------------|----------|
| Molecular Weight | 1336.38 g/mol | 1336.38 g/mol | |

| Thermal Properties | Metric | English | Comments | |
|---------------------------|---------|---------|----------|--|
| Melting Point | 2.00 °C | 35.6 °F | | |
| Decomposition Temperature | 359 °C | 678 °F | | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China