

Hyosung Topilene J642 PP

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Impact Modified; Molded/Extruded

Material Notes:

J642 Injection Impact Copolymer Applications: Washing M/C parts Electric appliance Characteristics: Medium impact High stiffness Information provided by Hyosung Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hyosung-Topilene-J642-PP.php

Physical Properties	Metric	English	Comments
Melt Flow	10 g/10 min	10 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	85	85	ASTM D785
Tensile Strength, Yield	28.4 MPa	4120 psi	ASTM D638
Elongation at Break	250 %	250 %	ASTM D638
Flexural Modulus	1.42 GPa	206 ksi	ASTM D790
Izod Impact, Unnotched	0.981 J/cm	1.84 ft-lb/in	ASTM D256
	0.490 J/cm @Temperature -10.0 Â°C	0.918 ft-lb/in @Temperature 14.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	120 Â°C	248 Â°F	ASTM D648
Vicat Softening Point	150 Â°C	302 Â°F	ASTM D1525
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China