

Hyosung Topilene R801H PP

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

R801H Injection Random Copolymer Applications: High transparent product Large articles Characteristics: High transparency Stiffness Information provided by Hyosung Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hyosung-Topilene-R801H-PP.php

Physical Properties	Metric	English	Comments
Melt Flow	30 g/10 min	30 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	85	85	ASTM D785
Tensile Strength, Yield	30.4 MPa	4410 psi	ASTM D638
Elongation at Break	500 %	500 %	ASTM D638
Flexural Modulus	1.13 GPa	164 ksi	ASTM D790
Izod Impact, Unnotched	0.490 J/cm	0.918 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	100 Â°C	212 Â°F	ASTM D648
Vicat Softening Point	130 Â°C	266 Â°F	ASTM D1525

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China