

IRPC Polimaxx Porene SP200 Acrylonitrile Butadiene Styrene

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

Applications: injection molding Helmets automotive electroplating painting articles

Order this product through the following link:

http://www.lookpolymers.com/polymer_IRPC-Polimaxx-Porene-SP200-Acrylonitrile-Butadiene-Styrene.php

Physical Properties	Metric	English	Comments
Melt Flow	17 g/10 min	17 g/10 min	ASTM D1238
	@Load 10.0 kg, Temperature 220 Â°C	@Load 22.0 lb, Temperature 428 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	109	109	ASTM D785
	@Thickness 6.35 mm, Temperature 23.0 Â°C	@Thickness 0.250 in, Temperature 73.4 Â°F	
Tensile Strength, Ultimate	41.2 MPa	5970 psi	ASTM D638
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Flexural Yield Strength	55.9 MPa	8110 psi	ASTM D790
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Flexural Modulus	2.01 GPa	292 ksi	ASTM D790
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Izod Impact, Notched	3.53 J/cm	6.61 ft-lb/in	ASTM D256
	@Thickness 6.35 mm, Temperature 23.0 Â°C	@Thickness 0.250 in, Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	90.0 Â°C	194 Â°F	ASTM D648
	@Thickness 6.35 mm	@Thickness 0.250 in	
Deflection Temperature at 1.8 MPa (264 psi)	84.0 Â°C	183 Â°F	ASTM D648
	@Thickness 6.35 mm	@Thickness 0.250 in	
Flammability, UL94	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Thermal Properties	HB Metric	HB English	Comments
	@Thickness 3.10 mm	@Thickness 0.122 in	

Processing Properties	Metric	English	Comments
Processing Temperature	190 - 240 Â°C	374 - 464 Â°F	
Drying Temperature	80.0 - 90.0 Â°C @Time 7200 - 18000 sec	176 - 194 Â°F @Time 2.00 - 5.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China