

ITW Devcon Metal Welder, Methacrylate Adhesive II, Grey / Beads

Category : Polymer , Adhesive , Thermoset , Methacrylate , Methacrylate Adhesive

Material Notes:

Information provided by ITW Devcon

Order this product through the following link:

http://www.lookpolymers.com/polymer_ITW-Devcon-Metal-Welder-Methacrylate-Adhesive-II-Grey-Beads.php

Physical Properties	Metric	English	Comments
Viscosity	90000 cP	90000 cP	Mixed Viscosity (Thixotropic gel)

Mechanical Properties	Metric	English	Comments
Elongation at Break	50 - 70 %	50 - 70 %	
Adhesive Bond Strength	17.97 MPa	2607 psi	lap shear; ASTM D1002
Tensile Impact Strength	>= 42.0 kJ/m ²	>= 20.0 ft-lb/in ²	
Peel Strength	5.26 - 7.01 kN/m	30.0 - 40.0 pli	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	93.3 Â°C	200 Â°F	dry
Minimum Service Temperature, Air	-55.0 Â°C	-67.0 Â°F	dry

Processing Properties	Metric	English	Comments
Cure Time	12.0 - 14.0 min	0.200 - 0.233 hour	Working time
	55.0 - 65.0 min	0.917 - 1.08 hour	Fixture time
	240 min	4.00 hour	Functional cure

Descriptive Properties	Value	Comments
Mix ratio (Resin:Hardener)	10:1	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China