

Ineos ABS Centrex® 833 ASA+AES Blend (discontinued **)

Category : Polymer , Thermoplastic , AES Polymer , ASA Polymer , Acrylonitrile/Styrene/Acrylate (ASA), Unreinforced, Molded

Material Notes:

Key Features: Unfilled High impact or high impact modified Light stabilized or stable to light U.V. stabilized or stable to weather Suitable processing methods: Profile extrusion Sheet extrusion Thermoforming Information provided by Bayer Polymers. LANXESS was spun-off from Bayer in early 2005. Business renamed Ineos ABS after INEOS acquires a majority shareholding under a JV with Lanxess in 2007. Subsequently Ineos acquired 100% of Ineos ABS.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-ABS-Centrex-833-ASAAES-Blend-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in ³	
Melt Flow	8.3 g/10 min @Load 10.0 kg, Temperature 220 °C	8.3 g/10 min @Load 22.0 lb, Temperature 428 °F	cm ³ /10 min.

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	28.5 MPa	4130 psi	
Elongation at Break	50 %	50 %	Nominal
Elongation at Yield	3.0 %	3.0 %	
Tensile Modulus	1.87 GPa	271 ksi	
Charpy Impact, Notched	3.81 J/cm ²	18.1 ft-lb/in ²	
	1.12 J/cm ² @Temperature -30.0 °C	5.33 ft-lb/in ² @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	101 µm/m-°C @Temperature 20.0 °C	56.1 µin/in-°F @Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	91.0 °C	196 °F	
Deflection Temperature at 1.8 MPa (264 psi)	77.0 °C	171 °F	
Vicat Softening Point	93.0 °C	199 °F	50°C/h 50N
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	UL Recognized

Thermal Properties	Metric	English	Comments
	@Thickness 3.00 mm	@Thickness 0.118 in	UL Recognized

Electrical Properties	Metric	English	Comments
Dissipation Factor	0.0116	0.0116	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	0.0123	0.0123	
	@Frequency 100 Hz	@Frequency 100 Hz	

Processing Properties	Metric	English	Comments
Melt Temperature	250 °C	482 °F	Injection Molding
Mold Temperature	60.0 °C	140 °F	Injection Molding
Injection Velocity	200 mm/sec	7.87 in/sec	
Injection Pressure	60.0 MPa	8700 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China