

Ineos ABS Lustran® H607AS

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Contains antistatic additives, Property data per ISO test methods.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-ABS-Lustran-H607AS.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	
Melt Flow	16 g/10 min @Load 10.0 kg, Temperature 220 °C	16 g/10 min @Load 22.0 lb, Temperature 428 °F	Estimated using room temperature density

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	46.0 MPa	6670 psi	
Elongation at Yield	2.5 %	2.5 %	
Tensile Modulus	2.40 GPa	348 ksi	
Charpy Impact Unnotched	13.0 J/cm ²	61.9 ft-lb/in ²	
	9.00 J/cm ² @Temperature -30.0 °C	42.8 ft-lb/in ² @Temperature -22.0 °F	
Charpy Impact, Notched	1.90 J/cm ²	9.04 ft-lb/in ²	
	0.900 J/cm ² @Temperature -30.0 °C	4.28 ft-lb/in ² @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	0.800 Åµm/m-Å°C @Temperature 20.0 Å°C	0.444 Åµin/in-Å°F @Temperature 68.0 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	101 Å°C	214 Å°F	
Deflection Temperature at 1.8 MPa (264 psi)	96.0 Å°C	205 Å°F	
Vicat Softening Point	100 Å°C	212 Å°F	
	HB	HB	

Thermal Properties	Metric	English	Comments
	@ Thickness 1.60 mm	@ Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	$\geq 1.00 \times 10^{15}$ ohm-cm	$\geq 1.00 \times 10^{15}$ ohm-cm	
Dielectric Constant	2.9	2.9	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	3.0	3.0	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	31.0 kV/mm	787 kV/in	
Dissipation Factor	0.0050	0.0050	
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0090	0.0090	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China