

Ineos ABS Lustran® SAN GF30 Glass Fiber Reinforced

Category : Polymer , Thermoplastic , SAN Polymer , Styrene Acrylonitrile (SAN), Molded, Glass Reinforced

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-ABS-Lustran-SAN-GF30-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.31 g/cc	0.0473 lb/in ³	ISO 1183
Linear Mold Shrinkage, Transverse	0.0020 - 0.0035 cm/cm	0.0020 - 0.0035 in/in	Test Condition: 150x105x3; acc. ISO 2577
Melt Flow	5.0 g/10 min @Load 10.0 kg, Temperature 220 °C	5.0 g/10 min @Load 22.0 lb, Temperature 428 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Elongation at Break	1.2 %	1.2 %	50 mm/min; ISO 527-1,-2
Tensile Modulus	11.0 GPa	1600 ksi	1 mm/min; ISO 527-1,-2
Flexural Strength	180 MPa	26100 psi	2 mm/min; ISO 178
Flexural Modulus	10.5 GPa	1520 ksi	2 mm/min; ISO 178

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	110 °C	230 °F	ISO 75-1,-2
Deflection Temperature at 1.8 MPa (264 psi)	107 °C	225 °F	ISO 75-1,-2
Vicat Softening Point	109 °C @Load 5.10 kg	228 °F @Load 11.2 lb	50 °C/hour; ISO 306
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China