

Ineos H48-500-199 Polyethylene Copolymer

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

Material Notes:

This is a high density polyethylene copolymer having a narrow molecular weight distribution. It is intended for roll-out cart applications.

This material meets the Food and Drug Administration requirements of 21CFR 177.1520. Information provided by Ineos Olefins & Polymers USA

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-H48-500-199-Polyethylene-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.948 g/cc	0.0342 lb/in ³	ASTM D4883
Environmental Stress Crack Resistance	24 hour	24 hour	Condition B, 10%; ASTM D1693
Melt Flow	5.5 g/10 min @Load 2.16 kg, Temperature 190 °C	5.5 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	65	65	ASTM D2240
Tensile Strength, Yield	22.8 MPa	3300 psi	2 in/min; ASTM D638
Elongation at Break	900 %	900 %	2 in/min; ASTM D638
Izod Impact, Notched	0.641 J/cm	1.20 ft-lb/in	ASTM D256
Tangent Modulus	965 MPa	140000 psi	ASTM D790

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	76.7 °C	170 °F	ASTM D648
Vicat Softening Point	128 °C	262 °F	ASTM D1525
Brittleness Temperature	<= -75.0 °C	<= -103 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China