

Ineos Nova 5460 High Impact Polystyrene (discontinued **)

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

High impact, Good environmental stress crack resistance, Good printabilityApplications: Thermoformed containers and lids, Hot and cold beverage cups, Custom sheetProperties were determined on injection molded specimens at 23°C and 50% R.H. unless otherwise specified.Information provided by NOVA Chemicals.INEOS NOVA began October 1 2007 as an expansion of the 50:50 joint venture between NOVA Chemicals and INEOS to include North American assets.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-Nova-5460-High-Impact-Polystyrene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in³	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ASTM D955
Melt Flow	3.0 g/10 min	3.0 g/10 min	Condition G

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	21.0 MPa	3050 psi	ASTM D638
Elongation at Break	50 %	50 %	ASTM D638
Flexural Yield Strength	29.0 MPa	4210 psi	ASTM D790
Flexural Modulus	1.65 GPa	239 ksi	ASTM D790
Izod Impact, Notched	1.23 J/cm @Diameter 3.17 mm	2.30 ft-lb/in @Diameter 0.125 in	bar, 0.010" notch radius; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	ASTM D648
Vicat Softening Point	100 °C	212 °F	ASTM D1525
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.51 @Frequency 1e+6 Hz	2.51 @Frequency 1e+6 Hz	
Dielectric Strength	15.7 kV/mm @Thickness 3.17 mm	400 kV/in @Thickness 0.125 in	

Electrical Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Melt Temperature	190 - 274 °C	374 - 525 °F	
Mold Temperature	38.0 - 82.0 °C	100 - 180 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China