

Ineos Nova 6260 Super High Impact Polystyrene (discontinued **)

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

Good toughness, Deep draw, Easy processing using all conventional methodsApplications: Thermoformed and molded packaging, Drink cups and lids, Structural foam, Custom sheetProperties were determined on injection molded specimens at 23°C and 50% R.H. unless otherwise specified.Information provided by NOVA Chemicals.INEOS NOVA began October 1 2007 as an expansion of the 50:50 joint venture between NOVA Chemicals and INEOS to include North American assets.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ineos-Nova-6260-Super-High-Impact-Polystyrene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ASTM D955
Melt Flow	3.0 g/10 min	3.0 g/10 min	Condition G

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	75	75	
Tensile Strength, Yield	25.0 MPa	3630 psi	ASTM D638
Elongation at Break	50 %	50 %	ASTM D638
Flexural Yield Strength	34.0 MPa	4930 psi	ASTM D790
Flexural Modulus	1.965 GPa	285.0 ksi	ASTM D790
Izod Impact, Notched	1.87 J/cm @Diameter 3.17 mm	3.50 ft-lb/in @Diameter 0.125 in	bar, 0.010" notch radius; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	ASTM D648
Vicat Softening Point	100 °C	212 °F	ASTM D1525
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.59 @Frequency 1e+6 Hz	2.59 @Frequency 1e+6 Hz	
	19.7 kV/mm	500 kV/in	

Dielectric Strength Electrical Properties	Metric @ Thickness 3.17 mm	English @ Thickness 0.125 in	Comments
--	-------------------------------	---------------------------------	----------

Processing Properties	Metric	English	Comments
Melt Temperature	190 - 274 °C	374 - 525 °F	
Mold Temperature	38.0 - 82.0 °C	100 - 180 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China