

Inno-Comp INNOPOLÂ® CS 1-3260 55% Chalk-Filled Polypropylene Homopolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Calcium Carbonate (CaCO3) Filler

Material Notes:

INNOPOLÂ® CS 1-3260 is a 55% chalk-filled polypropylene homopolymer compound /PP-H KD55 (ISO 1043)/. This grade is available in natural and custom colored form. INNOPOLÂ® CS 1-3260 is developed for producing injection molded components for household equipments. All information provided by INNO-COMP.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Inno-Comp-INNOPOL-CS-1-3260-55-Chalk-Filled-Polypropylene-Homopolymer.php

Physical Properties	Metric	English	Comments
Density	1.39 g/cc	0.0502 lb/inÂ³	ISO 1183
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Melt Flow	7.0 g/10 min	7.0 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 Â°C	@Load 4.76 lb, Temperature 446 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	21.0 MPa	3050 psi	50 mm/min; ISO 527-1,-2
Elongation at Yield	2.0 %	2.0 %	50 mm/min; ISO 527-1,-2
Tensile Modulus	3.30 GPa	479 ksi	1 mm/min; ISO 527-1,-2
Flexural Modulus	3.85 GPa	558 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	2.10 kJ/mÂ²	0.999 ft-lb/inÂ²	ISO 179/1eA
	@Temperature -20.0 Â°C	@Temperature -4.00 Â°F	
	3.80 kJ/mÂ²	1.81 ft-lb/inÂ²	ISO 179/1eA
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	123 Â°C	253 Â°F	ISO 75-1,-2

Descriptive Properties	Value	Comments
Color	Natural	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China