

Inno-Comp INNOPOLÂ® CS 2-3840 MO 40% Glass Filled Polypropylene Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Glass Fiber Filler

Material Notes:

INNOPOLÂ® CS 2-3840 MO is a 40 % glass-fiber-filled polypropylene block-copolymer compound. This grade is available in natural and custom colored form. INNOPOLÂ® CS 2-3840 MO is recommended for producing injection molded products, where the required properties are outstanding stiffness besides good impact strength. Information provided by INNO-COMP

Order this product through the following link:

http://www.lookpolymers.com/polymer_Inno-Comp-INNOPOL-CS-2-3840-MO-40-Glass-Filled-Polypropylene-Copolymer.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/inÂ³	ISO 1183
Melt Flow	10 g/10 min @Load 2.16 kg, Temperature 230 Â°C	10 g/10 min @Load 4.76 lb, Temperature 446 Â°F	nozzle diam 2.095 mm; ISO 1133
Storage Temperature	<= 60.0 Â°C	<= 140 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Stress	90.0 MPa	13100 psi	50 mm/min; ISO 527-1,-2
Elongation at Yield	2.5 %	2.5 %	50 mm/min; ISO 527-1,-2
Charpy Impact, Notched	1.20 J/cmÂ² @Temperature -20.0 Â°C	5.71 ft-lb/inÂ² @Temperature -4.00 Â°F	ISO 179/1eA
	1.40 J/cmÂ² @Temperature 23.0 Â°C	6.66 ft-lb/inÂ² @Temperature 73.4 Â°F	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	157 Â°C	315 Â°F	ISO 75-1,-2

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	190 - 240 Â°C	374 - 464 Â°F	Injection
Middle Barrel Temperature	190 - 240 Â°C	374 - 464 Â°F	Injection
Front Barrel Temperature	190 - 240 Â°C	374 - 464 Â°F	Injection
Melt Temperature	210 - 250 Â°C	410 - 482 Â°F	Injection

Processing Properties	Metric	English	Comments
Mold Temperature	15.0 - 50.0 A°C	59.0 - 122 A°F	
Moisture Content	<= 0.070 %	<= 0.070 %	

Descriptive Properties	Value	Comments
Resin Designation	PP-B GF40	ISO 1043

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China