

Intercontinental Polymers CoPET 214-02 CoPET Polymer Type - Clear, Low Melt Polyester Pellets

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), Unreinforced

Material Notes:

Applications: Low Melt Information provided by Intercontinental Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Intercontinental-Polymers-CoPET-214-02-CoPET-Polymer-Type-Clear-Low-Melt-Polyester-Pellets.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	0.62 - 0.68	0.62 - 0.68	Intrinsic; LCL-PR21

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	clear; thickness not quantified
Gardner Color Number	-1.00 - 4.0	-1.00 - 4.0	+ b; LCL-PR01
	25 - 41	25 - 41	Rd; LCL-PR01

Processing Properties	Metric	English	Comments
Melt Temperature	210 Â°C	410 Â°F	LCL-PR29
Moisture Content	<= 0.25 %	<= 0.25 %	LCL-PR08

Descriptive Properties	Value	Comments
COOH	Max 45 meq/kg	LCL-PR09
DEG	0.5 - 1.1 wt%	LCL-PR11
Isophthalic Acid	24 - 26 mol%	LCL-PR42

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China