

Isoflon PA 11 Polyamide 11

Category : Polymer , Thermoplastic , Nylon 11 , Nylon 11 , Unreinforced

Material Notes:

General use for mechanical parts Good heat resistance Easy to use Information provided by Isoflon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Isoflon-PA-11-Polyamide-11.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	DIN 53479
Water Absorption	0.80 %	0.80 %	ASTM D570

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	ASTM D785
Tensile Strength	44.0 MPa	6380 psi	DIN 53455
Elongation at Break	150 %	150 %	DIN 53455
Tensile Modulus	1.55 GPa	225 ksi	DIN 53457

Thermal Properties	Metric	English	Comments
CTE, linear	110 $\mu\text{m/m}^\circ\text{C}$	61.1 $\mu\text{in/in}^\circ\text{F}$	DIN 52328
Thermal Conductivity	0.300 W/m-K	2.08 BTU-in/hr-ft ² -°F	DIN 52612
Melting Point	185 °C	365 °F	DIN 53736
Maximum Service Temperature, Air	80.0 °C	176 °F	Continuous; DIN 52612
Deflection Temperature at 1.8 MPa (264 psi)	54.0 °C	129 °F	
Minimum Service Temperature, Air	-50.0 °C	-58.0 °F	Continuous; DIN 52612

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	DIN 53482
Dielectric Constant	3.5	3.5	DIN 53483
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Dielectric Strength	20.0 - 30.0 kV/mm	508 - 762 kV/in	DIN 53481

Descriptive Properties	Value	Comments
------------------------	-------	----------

Color Descriptive Properties	Mat Value	Comments
---------------------------------	--------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China