

KKPC Kuhmo MIB 237 Blow Molding HIPS

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

Key features: Good-profiling, Thin-layer Molding. **Common Uses:** It is used exclusively as a container for fermented milk beverages. HIPS is a functional resin made by copolymerization of styrene monomer and PBR. It shows excellent balance between impact-resistance and heat-resistance. Data provided by Korea Kumho Petrochemical Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_KKPC-Kuhmo-MIB-237-Blow-Molding-HIPS.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ASTM D792
Water Absorption	0.050 %	0.050 %	24 hr immersion; ASTM D570
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	ASTM D955
Melt Flow	8.5 g/10 min	8.5 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	70	70	ASTM D785
Tensile Strength, Ultimate	27.9 MPa	4050 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Flexural Yield Strength	43.49 MPa	6308 psi	ASTM D790
Flexural Modulus	1.860 GPa	269.8 ksi	ASTM D790
Izod Impact, Notched	0.892 J/cm @Thickness 3.20 mm	1.67 ft-lb/in @Thickness 0.126 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	74.0 Â°C	165 Â°F	unannealed; ASTM D648
Vicat Softening Point	98.0 Â°C	208 Â°F	ASTM D1525
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 2.20 mm	@Thickness 0.0866 in	
	HB	HB	

Thermal Properties	Metric @ Thickness 3.20 mm	English @ Thickness 0.126 in	Comments
--------------------	-------------------------------	---------------------------------	----------

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Strength	17.7 kV/mm	450 kV/in	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China