

Karina CAK 75-48/1 Black PVC Compound

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Vinyl (PVC) , PVC, Molded

Material Notes:

Reclaimed PVC compound recommended for soles injectionInformation provided by Karina Indústria e Comércio de Plásticos Ltda.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Karina-CAK-75-481-Black-PVC-Compound.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.27 - 1.37 g/cc	1.27 - 1.37 g/cc	ASTM D 792
ASTM Color	-1.02 - 0.58	-1.02 - 0.58	ASTM B, ME 12
	-0.720 - 0.88	-0.720 - 0.88	ASTM A, ME 12
	25.1 - 26.7	25.1 - 26.7	ASTM L, ME 12

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	73 - 77 @Time 15.0 sec	73 - 77 @Time 0.00417 hour	ASTM D 2240
Tensile Strength	>= 8.83 MPa	>= 1280 psi	ASTM D 638
Elongation at Break	>= 200 %	>= 200 %	ASTM D 638
Tear Strength	>= 40.0 kN/m	>= 228 pli	DIN 53507
Abrasion	<= 280	<= 280	mm³; DIN 53516

Descriptive Properties	Value	Comments
Application	General Purpose Soles	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China