

Karina E 5025/1-TRE Kariprene Natural

Category : Polymer , Thermoplastic

Material Notes:

Thermoplastic rubber compound, recommended for injection of footwear soles. Information provided by Karina Indústria e Comércio de Plásticos Ltda.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Karina-E-50251-TRE-Kariprene-Natural.php

Physical Properties	Metric	English	Comments
ASTM Color	-3.06 - -0.060	-3.06 - -0.060	ASTM A, ME 12
	-1.93 - 1.07	-1.93 - 1.07	ASTM B, ME 12
	84.8 - 87.8	84.8 - 87.8	ASTM L, ME 12

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	47 - 53	47 - 53	ASTM D 2240
	@Time 15.0 sec	@Time 0.00417 hour	
	68	68	After Injection Molding; ASTM D 2240
	@Time 15.0 sec	@Time 0.00417 hour	
Tensile Strength	>= 2.94 MPa	>= 427 psi	ASTM D 638
Elongation at Break	>= 350 %	>= 350 %	ASTM D 638
Tear Strength	>= 15.0 kN/m	>= 85.6 pli	DIN 53507
Abrasion	<= 300	<= 300	mm³; DIN 53516

Descriptive Properties	Value	Comments
Application	General Purpose Soles	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China