

Karina E TR-600N34/189-YT-AS Lilac 2562U

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Molded

Material Notes:

TR Compound, UV Radiation resistant, rubber additive, scented, recommended for general injection. Information provided by Karina Indústria e Comércio de Plásticos Ltda.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Karina-E-TR-600N34189-YT-AS-Lilac-2562U.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.17 - 1.23 g/cc	1.17 - 1.23 g/cc	ASTM D 792
ASTM Color	-20.66 - -18.66	-20.66 - -18.66	Color B, ME 12
	14.56 - 16.56	14.56 - 16.56	Color A, ME 12
	67.68 - 69.68	67.68 - 69.68	Color L, ME 12

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	58 - 62 @Time 15.0 sec	58 - 62 @Time 0.00417 hour	ASTM D 2240
Tensile Strength	>= 10.8 MPa	>= 1560 psi	ASTM D 638
Elongation at Break	>= 200 %	>= 200 %	ASTM D 638

Descriptive Properties	Value	Comments
Application	General Purpose Injection Molded Parts	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China